Supporting Information

A Mechanism for Non-stoichiometry in the Lithium Amide/Lithium Imide Hydrogen Storage Reaction

William I. F. David^{a,b}, Martin O. Jones^b, Duncan H. Gregory^c, Catherine M. Jewell^c,
Simon R. Johnson^b, Allan Walton^d and Peter P. Edwards^b

^a ISIS Facility, Rutherford Appleton Laboratory, Chilton, Didcot, Oxon., UK OX11 0QX.

^b Inorganic Chemistry Laboratory, University of Oxford, South Parks Road, Oxford, UK OX3 3QR

^c Department of Chemistry, University of Glasgow, Glasgow G12 8QQ, UK.

^d Department of Metallurgy and Materials, University of Birmingham, Edgbaston, Birmingham, B15 2TT.

Criteria of fit for the refinements are as follows;

Where $Y_{o,m}$ and $Y_{c,m}$ are the observed and calculated data respectively at each data point m , Bkg_m the background data point m , M the number of data points, P the number of parameters, w_m the weighting given to data point m which for counting statistics is given by $w_m = 1/\sigma(Y_{o,m})^2$ where $\sigma(Y_{o,m})$ is the error in $Y_{o,m}$ and $I_{o,k}$ and $I_{c,k}$ the “observed” and calculated intensities of the K^{th} reflection.

$$R_p = \sqrt{\frac{\sum |Y_{o,m} - Y_{c,m}|}{\sum Y_{o,m}}} \qquad R'_p = \sqrt{\frac{\sum |Y_{o,m} - Y_{c,m}|}{\sum |Y_{o,m} - Bkg_m|}}$$

$$R_{wp} = \sqrt{\frac{\sum W_m (Y_{o,m} - Y_{c,m})^2}{\sum W_m Y_{o,m}^2}} \qquad R'_{wp} = \sqrt{\frac{\sum W_m (Y_{o,m} - Y_{c,m})^2}{\sum W_m (Y_{o,m}^2 - Bkg_m^2)}}$$

$$R_{exp} = \sqrt{\frac{\sum M - P}{\sum W_m Y_{o,m}^2}} \qquad R'_{exp} = \sqrt{\frac{\sum M - P}{\sum W_m (Y_{o,m} - Bkg_m)^2}}$$

$$\text{Goodness of fit, GOF} = \chi^2 = \frac{R_{wp}}{R_{exp}} = \sqrt{\frac{\sum |I_{o,k} - I_{c,k}|}{\sum I_{o,k}}}$$

$$\text{“Durbin-Watson”, } d = \frac{\sum_{m=2}^M (\Delta Y_m - \Delta Y_{m-1})}{\sum_{m=1}^M (\Delta Y_m)^2}; \quad \Delta Y_m = Y_{o,m} - Y_{c,m}$$

Sample SI

R_expected	7.87	R_expected'	20.83
R_weighted pattern	9.16	R_weighted pattern'	24.26
R_Pattern	7.66	R_Pattern'	23.76
Weighted_Durbin_Watson	1.83		
Goodness of fit	1.16		

Phase Name*Li₃N***Space Group**

P6/mmm

Scale

0.00020(2)

Lattice Parameter

a = b = 3.6529(2), c = 3.8736(2) Å

Site	Li(1)	0.0	0.0	0.5	occ 1.0	b _{eq} 19(1)
Site	Li(2)	0.3333	0.6667	0.0	occ 1.0	b _{eq} 19(1)
Site	N	0.0	0.0	0.0	occ 1.0	b _{eq} 0.8(6)

Phase Name*Li_{2-x}NH_{1+x}***Space Group**

Fm3m

Scale

0.000114(6)

Lattice Parameter

a = b = c = 5.0542(1) Å

Site	Li	0.25	0.25	0.25	occ 0.575(3)	b _{eq} 1.4(9)
Site	N	0.0	0.0	0.0	occ 1.0	b _{eq} 5.5(5)

Phase Name*LiH(1)***Space Group**

Fm3m

Scale

0.00042(1)

Lattice Parameter

a = b = c = 4.08321(6) Å

Site	Li	0.0	0.0	0.0	occ 1.0	b _{eq} 0.88(5)
Site	H	0.5	0.5	0.5	occ 1.0	b _{eq} 2.0

Phase Name*LiH(2)***Space Group**

Fm3m

Scale

0.00121(1)

Lattice Parameter

a = b = c = 4.08410(4) Å

Site	Li	0.0	0.0	0.0	occ 1.0	b _{eq} 0.88(5)
Site	H	0.5	0.5	0.5	occ 1.0	b _{eq} 2.0

Phase Name*LiNH₂***Space Group**

I-4

Scale

0.000061(2)

Lattice Parameter

a = b = 5.04309(7), c = 10.2262(3) Å

Site	Li(1)	0.0	0.0	0.0	occ 1.0	b _{eq} 2.4(3)
Site	Li(2)	0.0	0.5	-0.25	occ 1.0	b _{eq} 2.4(3)
Site	Li(3)	0.0	0.5	0.003(4)	occ 1.0	b _{eq} 2.4(3)
Site	N	-0.234(2)	-0.246(5)	-0.1130(6)	occ 1.0	b _{eq} 0.9(2)
Site	H(1)	-0.23(2)	-0.18(2)	-0.194(9)	occ 1.0	b _{eq} 0.9(2)
Site	H(2)	-0.37(2)	-0.35(2)	-0.118(8)	occ 1.0	b _{eq} 0.9(2)

Phase Name*Li₂O***Space Group**

Fm3m

Scale

0.000031(6)

Lattice Parameter

a = b = c = 4.614(1) Å

Site	Li	0.25	0.25	0.25	occ 1.0	b _{eq} 0.5(9)
Site	O	0.5	0.5	0.5	occ 1.0	b _{eq} 6(3)

Sample SII

R_expected	7.45	R_expected'	20.95
R_weighted pattern	8.62	R_weighted pattern'	24.23
R_Pattern	7.24	R_Pattern'	23.14
Weighted_Durbin_Watson	1.80		
Goodness of fit	1.16		

Li-N-H-00 – Li-N-H-10 Lattice Parameter	a_hi = 5.07919(60)Å
Li-N-H-00 – Li-N-H-10 Lattice Parameter	a_lo = 5.00013(7)Å
Li-N-H-00 – Li-N-H-10 Li Occ. Parameter	xLi_hi = 0.828(12)
Li-N-H-00 – Li-N-H-10 Li Occ.Parameter	xLi_lo = 0.508(20)

Phase Name	<i>Li-N-H-00</i>						
Space Group	Fm3m						
Scale	0.001(1)						
Lattice Parameters	a = b = c = a_00 = 1.0*a_hi + 0.0*a_lo = 5.0792Å						
Occupancy Parameter	xLi_00 = 1.0*xLi_lo + 0.0*xLi_hi						
Site Li	0.25	0.25	0.25	occ (xLi_00)	0.5077	b _{eq}	1.4(1)
Site N	0.0	0.0	0.0	occ	1.0	b _{eq}	2.43(7)

Phase Name	<i>Li-N-H-01</i>						
Space Group	Fm3m						
Scale	0.030(8)						
Lattice Parameter	a = b = c = a_01 = 0.9*a_hi + 0.1*a_lo = 5.0713Å						
Occupancy Parameter	xLi_01 = 0.9*xLi_lo + 0.1*xLi_hi						
Site Li	0.25	0.25	0.25	occ (xLi_01)	0.5396	b _{eq}	1.4(1)
Site N	0.0	0.0	0.0	occ	1.0	b _{eq}	2.43(7)

Phase Name	<i>Li-N-H-02</i>						
Space Group	Fm3m						
Scale	0.163(9)						
Lattice Parameter	a = b = c = a_01 = 0.8*a_hi + 0.2*a_lo = 5.0634Å						
Occupancy Parameter	xLi_02 = 0.8*xLi_lo + 0.2*xLi_hi						
Site Li	0.25	0.25	0.25	occ (xLi_02)	0.5716	b _{eq}	1.4(1)
Site N	0.0	0.0	0.0	occ	1.0	b _{eq}	2.43(7)

Phase Name	<i>Li-N-H-03</i>						
Space Group	Fm3m						
Scale	0.175(9)						
Lattice Parameter	a = b = c = a_01 = 0.7*a_hi + 0.3*a_lo = 5.0555Å						
Occupancy Parameter	xLi_03 = 0.7*xLi_lo + 0.3*xLi_hi						
Site Li	0.25	0.25	0.25	occ (xLi_03)	0.6036	b _{eq}	1.4(1)
Site N	0.0	0.0	0.0	occ	1.0	b _{eq}	2.43(7)

Phase Name	<i>Li-N-H-04</i>						
Space Group	Fm3m						
Scale	0.239(9)						
Lattice Parameter	a = b = c = a_01 = 0.6*a_hi + 0.4*a_lo = 5.0476Å						
Occupancy Parameter	xLi_04 = 0.6*xLi_lo + 0.4*xLi_hi						
Site Li	0.25	0.25	0.25	occ (xLi_04)	0.6356	b _{eq}	1.4(1)
Site N	0.0	0.0	0.0	occ	1.0	b _{eq}	2.43(7)

Phase Name	<i>Li-N-H-05</i>						
Space Group	Fm3m						

Scale	0.239(9)						
Lattice Parameter	$a = b = c = a_{01} = 0.5 \cdot a_{hi} + 0.5 \cdot a_{lo} = 5.0397 \text{ \AA}$						
Occupancy Parameter	$xLi_{05} = 0.5 \cdot xLi_{lo} + 0.5 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_05)	0.6675	$b_{eq} 1.4(1)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(7)$

Phase Name	<i>Li-N-H-06</i>						
Space Group	Fm3m						
Scale	0.285(9)						
Lattice Parameter	$a = b = c = a_{01} = 0.4 \cdot a_{hi} + 0.6 \cdot a_{lo} = 5.0318 \text{ \AA}$						
Occupancy Parameter	$xLi_{06} = 0.4 \cdot xLi_{lo} + 0.6 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_06)	0.6995	$b_{eq} 1.4(1)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(7)$

Phase Name	<i>Li-N-H-07</i>						
Space Group	Fm3m						
Scale	0.333(10)						
Lattice Parameter	$a = b = c = a_{01} = 0.3 \cdot a_{hi} + 0.7 \cdot a_{lo} = 5.0239 \text{ \AA}$						
Occupancy Parameter	$xLi_{07} = 0.3 \cdot xLi_{lo} + 0.7 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_07)	0.7315	$b_{eq} 1.4(1)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(7)$

Phase Name	<i>Li-N-H-08</i>						
Space Group	Fm3m						
Scale	0.438(10)						
Lattice Parameter	$a = b = c = a_{01} = 0.2 \cdot a_{hi} + 0.8 \cdot a_{lo} = 5.0159 \text{ \AA}$						
Occupancy Parameter	$xLi_{08} = 0.2 \cdot xLi_{lo} + 0.8 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_08)	0.7635	$b_{eq} 1.4(1)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(7)$

Phase Name	<i>Li-N-H-09</i>						
Space Group	Fm3m						
Scale	0.738(18)						
Lattice Parameter	$a = b = c = a_{01} = 0.1 \cdot a_{hi} + 0.9 \cdot a_{lo} = 5.0080 \text{ \AA}$						
Occupancy Parameter	$xLi_{09} = 0.1 \cdot xLi_{lo} + 0.9 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_09)	0.7955	$b_{eq} 1.4(1)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(7)$

Phase Name	<i>Li-N-H-10</i>						
Space Group	Fm3m						
Scale	1.534(25)						
Lattice Parameter	$a = b = c = a_{01} = 0.0 \cdot a_{hi} + 1.0 \cdot a_{lo} = 5.00013 \text{ \AA}$						
Occupancy Parameter	$xLi_{10} = 0.0 \cdot xLi_{lo} + 1.0 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_10)	0.8274	$b_{eq} 1.4(1)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(7)$

Phase Name	<i>LiH</i>						
Space Group	Fm3m						
Scale	0.00102(2)						
Lattice Parameter	$a = b = c = 4.08321(2) \text{ \AA}$						
Site	Li	0.0	0.0	0.0	occ 1.0	$b_{eq} 0.92(7)$	
Site	H	0.5	0.5	0.5	occ 1.0	$b_{eq} 2.0$	

Phase Name	<i>Li₂O</i>						
Space Group	Fm3m						

Scale			0.000049(2)				
Lattice Parameter			a = b = c = 4.6124(1) Å				
Site	Li	0.25	0.25	0.25	occ 1.0	b _{eq} 1.8(3)	
Site	O	0.5	0.5	0.5	occ 1.0	b _{eq} 1.1(2)	

Sample SIII

R_expected	7.79	R_expected'	18.25
R_weighted pattern	9.43	R_weighted pattern'	22.10
R_Pattern	7.94	R_Pattern'	24.01
Weighted_Durbin_Watson	1.75		
Goodness of fit	1.21		

Li-N-H-00 – Li-N-H-10 Lattice Parameter	a_hi = 5.06992(40)Å
Li-N-H-00 – Li-N-H-10 Lattice Parameter	a_lo = 4.99957(6)Å
Li-N-H-00 – Li-N-H-10 Li Occ. Parameter	xLi_hi = 0.850(6)
Li-N-H-00 – Li-N-H-10 Li Occ. Parameter	xLi_lo = 0.590(10)

Phase Name	<i>Li-N-H-00</i>						
Space Group	Fm3m						
Scale	0.153(12)						
Lattice Parameter	a = b = c = a_00 = 1.0*a_hi + 0.0*a_lo = 5.0699Å						
Occupancy Parameter	xLi_00 = 1.0*xLi_lo + 0.0*xLi_hi						
Site Li	0.25	0.25	0.25	occ (xLi_00)	0.5894	b _{eq}	1.79(8)
Site N	0.0	0.0	0.0	occ	1.0	b _{eq}	2.43(4)

Phase Name	<i>Li-N-H-01</i>						
Space Group	Fm3m						
Scale	0.245(12)						
Lattice Parameter	a = b = c = a_01 = 0.9*a_hi + 0.1*a_lo = 5.0628Å						
Occupancy Parameter	xLi_01 = 0.9*xLi_lo + 0.1*xLi_hi						
Site Li	0.25	0.25	0.25	occ (xLi_01)	0.6156	b _{eq}	1.79(8)
Site N	0.0	0.0	0.0	occ	1.0	b _{eq}	2.43(4)

Phase Name	<i>Li-N-H-02</i>						
Space Group	Fm3m						
Scale	0.400(15)						
Lattice Parameter	a = b = c = a_01 = 0.8*a_hi + 0.2*a_lo = 5.0558Å						
Occupancy Parameter	xLi_02 = 0.8*xLi_lo + 0.2*xLi_hi						
Site Li	0.25	0.25	0.25	occ (xLi_02)	0.6417	b _{eq}	1.79(8)
Site N	0.0	0.0	0.0	occ	1.0	b _{eq}	2.43(4)

Phase Name	<i>Li-N-H-03</i>						
Space Group	Fm3m						
Scale	0.457(15)						
Lattice Parameter	a = b = c = a_01 = 0.7*a_hi + 0.3*a_lo = 5.0488Å						
Occupancy Parameter	xLi_03 = 0.7*xLi_lo + 0.3*xLi_hi						
Site Li	0.25	0.25	0.25	occ (xLi_03)	0.6678	b _{eq}	1.79(8)
Site N	0.0	0.0	0.0	occ	1.0	b _{eq}	2.43(4)

Phase Name	<i>Li-N-H-04</i>						
Space Group	Fm3m						
Scale	0.577(15)						
Lattice Parameter	a = b = c = a_01 = 0.6*a_hi + 0.4*a_lo = 5.0418Å						
Occupancy Parameter	xLi_04 = 0.6*xLi_lo + 0.4*xLi_hi						
Site Li	0.25	0.25	0.25	occ (xLi_04)	0.6940	b _{eq}	1.79(8)
Site N	0.0	0.0	0.0	occ	1.0	b _{eq}	2.43(4)

Phase Name	<i>Li-N-H-05</i>						
Space Group	Fm3m						

Scale	0.626(15)						
Lattice Parameter	$a = b = c = a_{01} = 0.5 \cdot a_{hi} + 0.5 \cdot a_{lo} = 5.0347 \text{ \AA}$						
Occupancy Parameter	$xLi_{05} = 0.5 \cdot xLi_{lo} + 0.5 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_05)	0.7201	$b_{eq} 1.79(8)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(4)$

Phase Name	<i>Li-N-H-06</i>						
Space Group	Fm3m						
Scale	0.756(18)						
Lattice Parameter	$a = b = c = a_{01} = 0.4 \cdot a_{hi} + 0.6 \cdot a_{lo} = 5.0277 \text{ \AA}$						
Occupancy Parameter	$xLi_{06} = 0.4 \cdot xLi_{lo} + 0.6 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_06)	0.7463	$b_{eq} 1.79(8)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(4)$

Phase Name	<i>Li-N-H-07</i>						
Space Group	Fm3m						
Scale	0.874(20)						
Lattice Parameter	$a = b = c = a_{01} = 0.3 \cdot a_{hi} + 0.7 \cdot a_{lo} = 5.0207 \text{ \AA}$						
Occupancy Parameter	$xLi_{07} = 0.3 \cdot xLi_{lo} + 0.7 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_07)	0.7724	$b_{eq} 1.79(8)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(4)$

Phase Name	<i>Li-N-H-08</i>						
Space Group	Fm3m						
Scale	1.251(20)						
Lattice Parameter	$a = b = c = a_{01} = 0.2 \cdot a_{hi} + 0.8 \cdot a_{lo} = 5.0136 \text{ \AA}$						
Occupancy Parameter	$xLi_{08} = 0.2 \cdot xLi_{lo} + 0.8 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_08)	0.7985	$b_{eq} 1.79(8)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(4)$

Phase Name	<i>Li-N-H-09</i>						
Space Group	Fm3m						
Scale	2.049(40)						
Lattice Parameter	$a = b = c = a_{01} = 0.1 \cdot a_{hi} + 0.9 \cdot a_{lo} = 5.0066 \text{ \AA}$						
Occupancy Parameter	$xLi_{09} = 0.1 \cdot xLi_{lo} + 0.9 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_09)	0.8247	$b_{eq} 1.79(8)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(4)$

Phase Name	<i>Li-N-H-10</i>						
Space Group	Fm3m						
Scale	4.186(50)						
Lattice Parameter	$a = b = c = a_{01} = 0.0 \cdot a_{hi} + 1.0 \cdot a_{lo} = 4.9996 \text{ \AA}$						
Occupancy Parameter	$xLi_{10} = 0.0 \cdot xLi_{lo} + 1.0 \cdot xLi_{hi}$						
Site	Li	0.25	0.25	0.25	occ (xLi_10)	0.8508	$b_{eq} 1.79(8)$
Site	N	0.0	0.0	0.0	occ	1.0	$b_{eq} 2.43(4)$

Phase Name	<i>LiH</i>						
Space Group	Fm3m						
Scale	0.00282(3)						
Lattice Parameter	$a = b = c = 4.0832(1) \text{ \AA}$						
Site	Li	0.0	0.0	0.0	occ 1.0		$b_{eq} 1.02(4)$
Site	H	0.5	0.5	0.5	occ 1.0		$b_{eq} 1.8(1)$

Phase Name	<i>Li₂O</i>						
Space Group	Fm3m						

Scale				0.000196(4)		
Lattice Parameter				a = b = c = 4.6128(4) Å		
Site	Li	0.25	0.25	0.25	occ 1.0	b _{eq} 2.5(2)
Site	O	0.5	0.5	0.5	occ 1.0	b _{eq} 1.0(1)

Supporting Information Figures

- Figure 1 The observed (dotted line), calculated (solid line) and difference plots ($Y_{\text{obs}} - Y_{\text{calc}}$, solid line in box) for the structure refinement of sample SII from X-ray synchrotron diffraction data collected at $\lambda = 0.8022\text{\AA}$ and with a step size of $0.003\text{\AA}$. The Bragg peak positions for LiH, all Li_2NH phases and Li_2O are all shown by the vertical tick marks. The complex microstructure and two-theta dependent strain broadening in these data can be observed on the low 2-theta sides of the Li_2NH diffraction peaks.
- Figure 2 The observed (dotted line), calculated (solid line) and difference plots ($Y_{\text{obs}} - Y_{\text{calc}}$, solid line in box) for the structure refinement of sample SIII from X-ray synchrotron diffraction data collected at $\lambda = 0.8022\text{\AA}$ and with a step size of $0.003\text{\AA}$. The Bragg peak positions for LiH, all Li_2NH phases and Li_2O are all shown by the vertical tick marks. The complex microstructure and two-theta dependent strain broadening in these data can be observed on the low 2-theta sides of the Li_2NH diffraction peaks.