Efficient Heterogeneous Asymmetric Transfer Hydrogenation of Ketones Using Highly Recyclable and Accessible Silica-Immobilized Ru-TsDPEN Catalysts

Pei Nian Liu, Pei Ming Gu, Fei Wang and Yong Qiang Tu *

*Department of Chemistry and State Key Laboratory of Applied Organic Chemistry
Lanzhou University, Lanzhou 730000, P. R. China.*

tuyq@lzu.edu.cn

Supporting Information

- 1. General.**
- 2. Synthesis of (1*R*,2*R*)-4.**
- 3. General procedure for the synthesis of immobilized ligands 5-7.**
- 4. Synthesis of the modified ligand 8.**
- 5. General procedure for the transfer hydrogenation of ketones using the immobilized catalysts.**
- 6. Determination of the leaching of Ru from the catalyst Ru-5 in the recycling reductions of acetophenone.**
- 7. Analytical data for obtained chiral aromatic alcohols.**
- 8. Reference.**

1. General:

Fomic acid-triethylamine azeotrope was prepared by adding triethylamine to fomic acid (ratio: 2:5) and then distilled under reduced pressure. Acetophenone was distilled from KMnO_4 and CH_2Cl_2 was distilled from CaH_2 . Triethylamine was distilled and stored avoiding light. $[\text{RuCl}_2(p\text{-cymene})]_2$ was prepared according to literature¹ and (1*R*,2*R*)-TsDPEN was prepared by standard method. Amorphous silica gel (60-100 mesh), mesoporous silicas of MCM-41 and SBA-15 were heated at 150 °C for 3 h and cooled under argon before use. Toluene was freshly distilled from a deep-blue solution of sodium-benzophenone under argon. Other reagents and chemicals were used as received. ^1H NMR and ^{13}C NMR spectra were recorded on Varian Mercury-plus 300 BB with TMS as internal standard. HRMS data were measured with ESI techniques (Bruker Apex II). Elemental analysis was performed on elementar vario EL and FT-IR spectra was performed on Nicolet NEXUS 670. The pore sizes and surface areas were determined on Micromeritics ASAP 2010 Accelerated Surface Area and Porosimetry System. The inductively coupled plasma atomic emission spectrometry (ICP-AES) was performed on Perkin-Elmer ICP/6500 inductively coupled plasma spectrometer. Optical rotation values were measured on Perkin-Elmer 341 polarimeter. Enantiomeric excess values were determined by GC with a CP-Chirasil-DEX CB column (25 m $\times$ 0.32 mm) on Varian CP-3800 or by HPLC with Chiralcel OB or OJ column on Agilent 1100 Series.

2. Synthesis of (1*R*,2*R*)-4:

(1*R*,2*R*)-DPEN **2** (0.636 g, 3.0 mmol) and triethylamine (0.6 mL) were dissolved in CH_2Cl_2 (30 mL), and 2-(4-chlorosulfonylphenyl)ethyltrimethoxysilane **3** (0.75 g, 2.31 mmol) in CH_2Cl_2 (30 mL) was

then added dropwise at 0 °C. The reaction mixture was then allowed to warm to room temperature slowly and stirred for 3 h. After the solvent was removed in vacuo, the residue was fast passed through a short column (silica gel, eluent: Et₃N:CH₃OH:CH₂Cl₂ = 1:10:100) and concentrated in vacuo to afford (*R,R*)-**4** as beige glass.

Yield: 86%; $[\alpha]_D^{20}$ -36 (*c* 0.8, CH₂Cl₂); ¹H NMR (300 MHz, CDCl₃) δ 0.89-0.95 (m, 2H), 1.50 (s, 2H, NH₂), 2.65-2.70 (m, 2H), 3.59 (s, 9H), 4.12 (d, *J* = 5.4 Hz, 1H), 4.37 (d, *J* = 5.4 Hz, 1H), 6.99-7.34 (m, 14H); ¹³C NMR (75 MHz, CDCl₃) δ 11.0, 28.5, 50.6, 60.4, 63.2, 126.5, 126.9, 127.3, 127.4, 127.8, 128.2, 128.3, 137.3, 139.1, 141.3, 148.8; IR 3352, 3296, 3171, 3060, 3028, 2941, 2841, 1902, 1691, 1600, 1495, 1454, 1410, 1343, 1322, 1265, 1191, 1157, 1088, 1013 cm⁻¹; ESI-HRMS, calcd for C₂₅H₃₂N₂O₅SSi + H⁺ 501.1874, found 501.1881.

3. General procedure for the synthesis of immobilized ligands 5-7:

The predried silica (3 g) and ligand (*R,R*)-**4** (0.25 g) were added to dry toluene (40 mL) and the mixture was refluxed for 24 h under argon. After filtration, the white solid was washed by toluene (60 mL), mixture solvent of CH₂Cl₂ and CH₃OH (1:1, 100 mL). Then the solid was suspended in the mixture solvent (CH₂Cl₂:CH₃OH = 1:1, 50 mL) and stirred overnight. After filtration and thorough wash with the mixture solvent (CH₂Cl₂:CH₃OH = 1:1, 50 mL) and CH₃OH (50 ml), the solid was dried at 60 °C in vacuo for 24 h to give the immobilized ligand.

Ligand 5: IR 3440, 2960, 1642, 1509, 1464, 1097, 801, 702, 559, 469 cm⁻¹; elemental analysis: N 0.41, C 4.71, S 0.48, H 0.59; average pore size: 90.2 Å; S_{BET}: 324 m²/g.

Ligand 6: IR 3442, 2962, 2860, 1627, 1461, 1081, 812, 698, 455 cm^{-1} ; elemental analysis: N 0.38, C 6.52, S 0.47, H 1.04; pore size: 18.7 Å; S_{BET} : 1150 m^2/g .

Ligand 7: IR 3438, 2958, 2856, 1635, 1462, 1084, 811, 701, 462 cm^{-1} ; elemental analysis: N 0.28, C 5.74, S 0.31, H 0.54; pore size: 61.8 Å; S_{BET} : 497 m^2/g .

4. Synthesis of the modified ligand 8:

Immobilized ligand **5** (0.3 g) was added to hexamethyldisiloxane (HMDSO, 10 mL) and the mixture was refluxed for 18 h under argon. After filtration and thorough wash with CH_3OH (30 mL), the solid was dried at 60 °C in vacuo for 24 h to give ligand **8**.

Ligand 8: IR 3439, 2970, 2845, 1637, 1460, 1095, 965, 802, 700, 467 cm^{-1} ; elemental analysis: N 0.33, C 5.55, S 0.41, H 1.10; average pore size: 87.4 Å; S_{BET} : 313 m^2/g .

5. General procedure for the transfer hydrogenation of ketones using the immobilized catalysts:

Immobilized ligand (0.0068 mmol), $[\text{RuCl}_2(p\text{-cymene})]_2$ (0.002 mmol) and triethylamine (0.016 mmol) were stirred in dry CH_2Cl_2 (0.4 mL) for 1 h under argon at 28 °C. Then the formic acid-triethylamine azeotrope (0.2 mL) and the ketone (0.4 mmol) were added and the mixture was stirred at 40 °C and monitored by TLC. After the completion of the reaction, dry CH_2Cl_2 (1 mL) was added and the mixture was stirred for 1 min, then the reactor was centrifuged (2000 r/min) for 1-2 min and the solution was removed with syringe. The catalyst was then washed with CH_2Cl_2 (1 mL) twice and CH_2Cl_2 was removed; a new reaction could be conducted by adding formic

acid-triethylamine azeotrope (0.2 mL) and ketone (0.4 mmol) in turn to the recovered catalyst. The solution containing the product was fast passed through a short column (silica gel, eluent: Et₂O) and the conversion and the ee value were then determined by chiral GC on CP-Chirasil-DEX CB column (25 m × 0.32 mm) or by HPLC with Chiralcel OB or OJ column on Agilent 1100 Series.

6. Determination of the leaching of Ru from the catalyst Ru-5 in the recycling reductions of acetophenone.

The predried recovered catalyst Ru-5 (50.0 mg) with the powder mixture of KOH (1.0 g) and KNO₃ (0.2 g) was heated to 650 °C for 5-10 min, then cooled, dissolved in hot water and added 12 M HCl (4 mL) to acidify the solution, then the solution was diluted to 50.0 mL and the amount of metal Ru was determined by ICP-AES.

The leached Ru in organic solutions after the reaction was dissolved in 0.3 M HCl (10 mL) and determined by ICP-AES.

Ru/SiO₂ (weight): before use: 0.54%, after 5 uses: 0.35%.

Amount of leached Ru in organic solutions: after the 1st run: 11 µg, after the 2nd run: 15 µg, after the 3rd run: 17 µg, after the 4th run: 24 µg, after the 5th run: 34 µg.

7. Analytical data for obtained chiral aromatic alcohols:

$[\alpha]_D^{28} +52$ (c 1.1, CHCl_3); ^1H NMR (300 MHz, CDCl_3 , 97% ee) δ 1.45 (d, $J = 6.6$ Hz, 3H), 2.29 (s, 1H, OH), 4.80-4.86 (m, 1H), 7.23-7.35 (m, 5H); ^{13}C NMR (75 MHz, CDCl_3) δ 25.0, 70.2, 125.3, 127.3, 128.4, 145.8; GC analysis: CP-Chirasil-DEX CB column (25 m $\times$ 0.32 mm), column temperature = 126 $^\circ\text{C}$, (isothermal), injector temperature = 250 $^\circ\text{C}$, detector temperature (FID) = 300, carrier gas: N_2 , inlet pressure = 7 psi; $t_R = 8.1$ min, $t_S = 8.8$ min.

$\text{C}_8\text{H}_9\text{FO}$, FW = 140.15

$[\alpha]_D^{28} +36$ (c 1.8, CHCl_3 , 94% ee); ^1H NMR (300 MHz, CDCl_3) δ 1.42-1.45 (m, 3H), 2.69 (s, 1H, OH), 4.78-4.85 (m, 1H), 6.89-6.96 (m, 1H), 7.03-7.09 (m, 2H), 7.23-7.31 (m, 1H); ^{13}C NMR (75 MHz, CDCl_3) δ 25.1, 69.6, 112.1, 112.4, 113.9, 114.2, 120.9, 129.8, 129.9, 148.4, 148.5, 161.3, 164.5; GC analysis: CP-Chirasil-DEX CB column (25 m $\times$ 0.32 mm), column temperature = 135 $^\circ\text{C}$, (isothermal), injector temperature = 250 $^\circ\text{C}$, detector temperature (FID) = 300, carrier gas: N_2 , inlet pressure = 7 psi; $t_R = 8.6$ min, $t_S = 9.6$ min

$\text{C}_8\text{H}_9\text{FO}$, FW = 140.15

$[\alpha]_D^{28} +38$ (c 1.2, CHCl_3 , 93% ee); ^1H NMR (300 MHz, CDCl_3) δ 1.53 (d, $J = 6.6$ Hz, 3H), 2.20 (s, 1H, OH), 4.96-5.03 (m, 1H), 7.43-7.47 (m, 2H), 7.75-7.80 (m, 2H); ^{13}C NMR (75 MHz, CDCl_3) δ 25.0, 70.4, 123.8, 125.7, 126.1, 127.6, 127.9, 128.2, 132.8, 133.3, 143.2; GC analysis: CP-Chirasil-DEX CB column (25 m $\times$ 0.32 mm), column temperature = 127 $^\circ\text{C}$, (isothermal), injector temperature = 250 $^\circ\text{C}$, detector temperature (FID) = 300, carrier gas : N_2 , inlet pressure = 7 psi; $t_R = 9.7$ min, $t_S = 10.5$ min.

$\text{C}_8\text{H}_9\text{ClO}$, FW = 156.61

$[\alpha]_{\text{D}}^{28} +54$ (*c* 2.3, CHCl_3 , 94% ee); ^1H NMR (300 MHz, CDCl_3) δ 1.42-1.45 (m, 3H), 2.78 (s, 1H, OH), 5.22-5.26 (m, 1H), 7.12-7.30 (m, 3H), 7.53-7.55 (m, 1H); ^{13}C NMR (75 MHz, CDCl_3) δ 23.4, 66.7, 126.3, 127.1, 128.2, 129.2, 131.4, 143.0; GC analysis: CP-Chirasil-DEX CB column (25 m $\times$ 0.32 mm), column temperature = 160 $^\circ\text{C}$, (isothermal), injector temperature = 250 $^\circ\text{C}$, detector temperature (FID) = 300, carrier gas: N_2 , inlet pressure = 7 psi; t_{R} = 7.2 min, t_{S} = 7.8 min.

$\text{C}_8\text{H}_9\text{BrO}$, FW = 201.06

$[\alpha]_{\text{D}}^{28} +48$ (*c* 1.7, CHCl_3 , 93% ee); ^1H NMR (300 MHz, CDCl_3) δ 1.42 (d, J = 6.3 Hz, 3H), 2.81 (s, 1H, OH), 5.14-5.20 (m, 1H), 7.08 (t, J = 7.5 Hz, 1H), 7.30 (t, J = 7.2 Hz, 1H), 7.45-7.54 (m, 2H); ^{13}C NMR (75 MHz, CDCl_3) δ 23.5, 69.0, 121.5, 126.6, 127.7, 128.6, 132.5, 144.6; GC analysis: CP-Chirasil-DEX CB column (25 m $\times$ 0.32 mm), column temperature = 170 $^\circ\text{C}$, (isothermal), injector temperature = 250 $^\circ\text{C}$, detector temperature (FID) = 300, carrier gas: N_2 , inlet pressure = 7 psi; t_{R} = 6.5 min, t_{S} = 7.3 min.

$\text{C}_9\text{H}_{12}\text{O}_2$, FW = 152.19

$[\alpha]_{\text{D}}^{28} +39$ (*c* 1.0, CHCl_3 , 96% ee); ^1H NMR (300 MHz, CDCl_3) δ 1.48 (d, J = 6.3 Hz, 3H), 2.02 (s, 1H, OH), 3.81 (s, 3H), 4.82-4.88 (m, 1H), 6.79-6.82 (m, 1H), 6.92-6.95 (m, 2H), 7.25 (t, J = 8.4 Hz, 1H); ^{13}C NMR (75 MHz, CDCl_3) δ 25.1, 55.2, 70.3, 110.9, 112.9, 117.7, 129.5, 147.6, 159.8; GC analysis: CP-Chirasil-DEX CB column (25 m $\times$ 0.32 mm), column temperature = 146 $^\circ\text{C}$, (isothermal), injector temperature = 250 $^\circ\text{C}$, detector temperature (FID) = 300, carrier gas: N_2 , inlet

pressure = 7 psi; t_R = 11.0 min, t_S = 11.7 min.

$[\alpha]_D^{28}$ -32 (c 1.0, $CHCl_3$); 1H NMR (300 MHz, $CDCl_3$, >99% ee) δ 1.26-1.99 (m, 4H), 2.71-2.84 (m, 2H), 4.75 (t, J = 4.2 Hz, 1H), 7.07-7.10 (m, 1H), 7.16-7.23 (m, 2H), 7.39-7.42 (m, 1H); ^{13}C NMR (75 MHz, $CDCl_3$) δ 18.8, 29.2, 32.2, 68.1, 126.1, 127.5, 128.6, 128.9, 137.0, 138.8; HPLC analysis: Chiralcel OB column, 2-propanol:hexane = 2.2:97.8 (1.0 mL/min), t_R = 11.3 min, t_S = 16.6 min.

Mp: 69-70 °C; $[\alpha]_D^{28}$ -31 (c 1.3, $CHCl_3$, >99% ee); 1H NMR (300 MHz, $CDCl_3$) δ 1.87 (s, 1H, OH), 1.90-1.99 (m, 1H), 2.42-2.53 (m, 1H), 2.76-2.86 (m, 1H), 3.00-3.10 (m, 1H), 5.23 (s, 1H), 7.22-7.25 (m, 3H), 7.39-7.42 (m, 1H); ^{13}C NMR (75 MHz, $CDCl_3$) δ 29.8, 35.9, 76.4, 124.2, 124.9, 126.7, 128.3, 143.3, 145.0. HPLC analysis: Chiralcel OB column, 2-propanol:hexane = 5:95 (1.0 mL/min), t_R = 8.4 min, t_S = 12.1 min.

Mp: 68-70 °C; $[\alpha]_D^{28}$ +46 (c 1.1, $CHCl_3$, 95% ee); 1H NMR (300 MHz, $CDCl_3$) δ 1.47-1.50 (m, 3H), 2.28 (s, 1H, OH), 5.13-5.19 (m, 1H), 6.95-7.03 (m, 1H), 7.09-7.26 (m, 4H), 7.43-7.48 (m, 2H); ^{13}C NMR (75 MHz, $CDCl_3$) δ 23.9, 64.4, 115.1, 115.3, 124.3, 126.6, 128.6, 128.7, 130.9, 132.5, 158.0, 161.4; HPLC analysis: Chiralcel OJ column, 2-propanol:hexane = 7:93 (1.0 mL/min), t_S = 18.6 min, t_R = 23.8 min.

$[\alpha]_{\text{D}}^{28} +9$ (c 1.4, CHCl_3 , 96% ee); ^1H NMR (300 MHz, CDCl_3) δ 1.54 (d, J = 6.6 Hz, 3H), 4.85-4.91 (m, 1H), 6.23 (d, J = 3 Hz, 1H), 6.32-6.33 (m, 1H), 7.37 (d, J = 1.2 Hz, 1H); ^{13}C NMR (75 MHz, CDCl_3) δ 21.2, 63.6, 105.1, 110.1, 141.9, 157.6; GC analysis: CP-Chirasil-DEX CB column (25 m $\times$ 0.32 mm), column temperature: 60 $^\circ\text{C}$ hold 0.1 min, ramp 3/min to 87 $^\circ\text{C}$ hold 3 min, injector temperature = 250 $^\circ\text{C}$, detector temperature (FID) = 300, carrier gas: H_2 , inlet pressure = 7 psi; t_{R} = 9.8 min, t_{S} = 10.4 min.

$[\alpha]_{\text{D}}^{28} +58$ (c 1.1, CHCl_3 , 97% ee); ^1H NMR (300 MHz, CDCl_3) δ 2.69 (d, J = 6.0 Hz, 2H), 3.17 (s, 1H, OH), 4.96 (t, J = 6.0 Hz, 1H), 7.30-7.40 (m, 5H); ^{13}C NMR (75 MHz, CDCl_3) δ 27.8, 69.8, 117.4, 125.5, 128.6, 128.8, 141.0; HPLC analysis: Chiralcel OJ column, 2-propanol:hexane = 10:90 (1.0 mL/min), t_{S} = 22.0 min, t_{R} = 26.5 min.

8. Reference: (1) Bennett, M. A.; Smith, A. K. *J. Chem. Soc., Dalton Trans.*, **1974**, 233.