Supporting Information

Insight into the catalytic mechanism of bimetallic platinum-copper core-shell nanostructures for nonaqueous oxygen evolution reactions

Lu Ma,^{1‡} Xiangyi Luo,^{2‡} A. Jeremy Kropf,³ Jianguo Wen,⁴ Xiaoping Wang,³ Sungsik Lee,¹ Deborah J. Myers,³ Dean Miller,⁴ Tianpin Wu,^{1} Jun Lu^{3*}, and Khalil Amine^{3*}*

¹ *X-ray Science Division, Argonne National Laboratory, 9700 South Cass Avenue, Argonne, IL 60439.*

² *Material Science Division, Argonne National Laboratory, 9700 South Cass Avenue, Argonne, IL 60439.*

³ *Chemical Sciences and Engineering Division, Argonne National Laboratory, 9700 South Cass Avenue, Argonne, IL 60439.*

⁴ *Electron Microscopy Center - Center for Nanoscale Materials, Argonne National Laboratory, 9700 South Cass Avenue, Argonne, IL 60439.*

Corresponding Author

*To whom correspondence should be addressed.

Jun Lu: Email: junlu@anl.gov; Phone: 630-252-4485

Tianpin Wu: Email: twu@aps.anl.gov; Phone: 630-252-1482

Khalil Amine: Email: amine@anl.gov; Phone: 630-252-3838

1. Experimental details

1.1 Synthesis of the Pt-Cu core-shell nanoparticles

Vulcan XC-72 carbon powder (Cabot Corporation) was used as support for preparing the carbon-supported Cu, Pt, or Pt-Cu catalysts. The Cu and Pt salts used were $\text{Cu}(\text{NO}_3)_2 \cdot 3\text{H}_2\text{O}$ and H_2PtCl_6 , respectively. The precursors were dissolved in deionized water (Millipore, 18 M Ω) and then mixed with a pre-determined amount of Vulcan XC-72 to achieve the desired weight loading of metal(s) on the support. The volume of water used for dissolving the salts exceeded that necessary to fill the pores of the Vulcan XC-72 support (i.e., wet impregnation technique). After stirring for 2 hours, the slurry mixture was vacuum dried at 70°C for 3 hours. The final catalysts were formed by treating the dried samples for 2 hours in a dilute hydrogen atmosphere (3.5% H_2 in an inert gas) at a temperature of 150 -250°C.

1.2 High-energy X-ray Diffraction

The X-ray diffraction (XRD) measurement of the cathode laminates after discharge was carried out on beamline 11-ID-C at APS. The X-ray wavelength was 0.1725 Å. The XRD two-dimensional patterns were collected in the transmission mode using a Perkin Elmer large area detector, and then integrated into conventional one-dimensional patterns (intensity versus 2θ) for analysis using the Fit2d software.

1.3 Scanning Electron Microscopy

The field-emission scanning electron microscope (FESEM, Hitachi S-4700) was used to characterize the morphology of the discharge product and the cathode surface. The samples were protected from exposure to air during transferring to the SEM chamber by a conductive tape applied in the glove box.

1.4 Transmission Electron Microscopy

(Scanning) transmission electron microscopy was carried out using a FEI Titan 80-300 ST transmission electron microscope with a spherical and chromatic aberration-corrected image corrector operating at 80 keV. Thin specimens for TEM analysis were prepared by dispersing powders onto a holey carbon coated grid.

1.5 X-ray Absorption Data Collection.

X-ray absorption data was collected at the Advanced Photon Source (APS) on beamline 10-BM (MRCAT) with electron energy 7GeV with average current of 100mA. The radiation was monochromatized by a Si (111) crystal monochromator. The monochromator was detuned 50% for harmonic rejection. All spectra were recorded by transmission mode. For energy calibration, a piece of copper or platinum foil was measured simultaneously at the reference ionization chamber in transition mode at Cu K-edge and Pt L₃-edge, respectively. The energy scale was adjusted to the tabulated values: Cu metal foil with $E_0=8979$ eV and Pt metal foil with $E_0=11564$ eV. The spectra of commercial Cu₂O and CuO were also recorded as standard materials.

1.6 XAS Data Analysis

Athena software was used for data processing (energy calibration, background subtraction and normalization). The linear combination was also fitted with Athena. The structural information was obtained by fitting the EXAFS with Artemis. The scattering paths were calculated with feffv9. The EXAFS coordination parameters were obtained by fitting in k-space of the k^3 -weighted Fourier transform data: $k=2.0-13.4 \text{ \AA}^{-1}$ for Cu K-edge and $k=3.0-14.5 \text{ \AA}^{-1}$ for Pt L₃-edge. The first-shell fitting was performed between 1.4 and 2.8 $\text{\AA}$ for the Cu K-edge and 1.5-3.2 $\text{\AA}$ for the Pt L₃-edge.

1.7 SAXS measurement

Measurements were performed at 12-BM at the Advanced Photon Source (APS), Argonne National Laboratory. The 2D SAXS data were collected on the Mar165 CCD detector (Rayonix, LLC.), a q range of $0.01 - 0.4 \text{ \AA}^{-1}$ with an incident energy of 11.54 keV ($\lambda = 1.074 \text{ \AA}$). The scattering vector, Q , was calibrated using a silver behenate. Quantitative data analyses were performed using spheroid form factors with a Schulz–Zimm distribution implemented in the Irena package within Igor Pro.¹

1.8 Li-O₂ cell assembling

All cells were assembled in an argon gas-filled glovebox. The cathode material (Pt-Cu on carbon) (80 wt%) and polyvinylidene fluoride (PVDF, 20 wt%) were mixed in a 1-methyl-2-pyrrolidinone (NMP, Aldrich) solution to make the slurry. The slurry was coated on carbon paper (TGP-H-030, Torray) and dried at 100 °C for 12 hours in a vacuum. The loading of the active material was $0.70 \pm 0.15 \text{ mg}$. The cells were assembled in a Swagelok cell configuration with a piece of lithium foil (thickness, manufacturer?) as anode (7/16 inch diameter), a piece of glass fiber as separator (1/2 inch diameter, saturated by the electrolyte of 1M lithium triflate (LiCF_3SO_3 , Aldrich) in a tetraethylene glycol dimethyl ether (TEGDME)solvent), the cathode and a piece of aluminum mesh as current collector. After assembling, the cell was purged with pure oxygen for 30 minutes before testing.

1.9 Electrochemical measurements

The Li-O₂ cells were tested by a MACCOR cyclor within a voltage range between 2.2V and 4.5 V and the discharge and current was set to a constant current density of 100 mA/gcarbon. The observed capacity was normalized by the weight of the active material on cathode for comparison.

1.10 X-ray Photoelectron Spectroscopy (XPS)

The XPS spectra was calibrated by C 1s at 285 eV. Cu 2p line was fitted with GL(80) line-shape (Gaussian 20 %-Lorentzian80 %) by casaXPS. The fitting parameters were based on the reported values.²

2. Linear combination fitting result.

Cu K-edge (in air)	XANES fit (-10, +30eV)		Cu K-edge (in air)	XANES fit (-10, +30eV)	
	5% Cu	10%Pt+5%Cu		Cu(I) oxide	Cu(II) oxide
2.5%Pt+5%Cu	0	1	5%Cu	0.307	0.693
5%Pt+5%Cu	0	1	2.5%Pt+5%Cu	0	1
			5%Pt+5%Cu	0	1
			10%Pt+5%Cu	0	1

Table S1. LCF result of Cu K-edge XANES of Pt-Cu catalysts in air. (left) The 5%Cu (in air) and 10%Pt+5%Cu (in air) were chosen as standards and (right) Cu(I) oxide and Cu(II) oxide were used as standards.

3. White line intensity of Pt L₃-edge by fitting the XANES spectra.

The white line intensity of the Pt L₃-edge was analyzed by curve fitting the XANES spectra with an arctangent function and a Gaussian function by Athena software. Figure S1 shows a

typical curve fitting for the XANES spectra. The summary of the white line intensity height of different catalysts is in Table S2.

Figure S1. Fitting result of XANES spectra of 2.5%Pt+5%Cu catalyst.

Samples	White line intensity (a.u.)
2.5% Pt	4.868
2.5%Pt+5% Cu	4.970
Pt foil	2.348
PtO ₂	12.949

Table S2. Summary of the white line intensity of different catalysts with the standard Pt and PtO₂.

4. Fitting parameters of EXAFS

Sample	Edge	Scatter	$N \cdot S_0^2$	R (Å)	σ^2 (Å ²)	E_0 (eV)
2.5%Pt+5%Cu	Cu K	Cu-Cu	7.40	2.536±0.002	0.0114±0.0003	-1.4
		Cu-Pt	0.30	2.601±0.014	0.0009±0.0017	-5.2
		Cu-M	7.70			
	Pt L ₃	Pt-Cu	5.66	2.601±0.014	0.0009±0.0017	0.3
		Pt-Pt	4.96	2.707±0.011	0.0064±0.0013	3.1
		Pt-M	10.62			
5%Cu	Cu K	Cu-Cu	7.50	2.534±0.002	0.0133±0.0004	-1.8
2.5%Pt	Pt L ₃	Pt-Pt	7.81	2.714±0.005	0.0104±0.0006	-0.66667
Cu K: $\Delta k=2.0-13.4 \text{ Å}^{-1}$ and $\Delta R=1.4-2.8 \text{ Å}$; Pt L ₃ : $\Delta k=3.0-14.5 \text{ Å}^{-1}$ and $\Delta R=1.5-3.2 \text{ Å}$. $\Delta N=\pm 10\%$						

Table S3. Fitting parameters of the Fourier Transform of the first shell of the k^3 -weighted EXAFS spectra, where N is the coordination number, S_0^2 is the amplitude reduction factor, R is the bond distance, σ^2 is the Debye-Waller factor and E_0 is the edge energy shift.

5. Analysis of the extents of alloying Pt and Cu

The extents of alloying of Pt and Cu were calculated from the EXAFS-derived coordination numbers and from the coordination numbers expected for complete and random alloying (i.e., random dispersion of Cu and Pt throughout the particles). As defined by Hwang *et al.*, the extent of alloying of Pt (J_{Pt}) is:

$$J_{Pt} = \frac{P_{Pt,observed}}{P_{Pt,random}} \times 100\% \quad (1)$$

where,

$$P_{Pt,observed} = \frac{N_{Pt-Cu}}{N_{Pt-Pt} + N_{Pt-Cu}} \quad (2)$$

$$P_{Pt,random} = \frac{N_{Pt-Cu,random}}{N_{Pt-Pt,random} + N_{Pt-Cu,random}} = \frac{n_{Cu}}{n_{Cu} + n_{Pt}} \quad (3)$$

The extent of alloying of Cu (J_{Cu}) is:

$$J_{Cu} = \frac{P_{Cu,observed}}{P_{Cu,random}} \times 100\% \quad (4)$$

where,

$$P_{Cu,observed} = \frac{N_{Cu-Pt}}{N_{Cu-Cu} + N_{Cu-Pt}} \quad (5)$$

$$P_{Cu,random} = \frac{N_{Cu-Pt,random}}{N_{Cu-Cu,random} + N_{Cu-Pt,random}} = \frac{n_{Pt}}{n_{Cu} + n_{Pt}} \quad (6)$$

where, n_{Pt} and n_{Cu} are the number of moles of Pt and Cu, respectively.

The mole fractions of Cu and Pt determined from the as-fabricated ratios were used to calculate P_{random} . The $P_{Pt,random}$ and the $P_{Cu,random}$ for the 2.5%Pt+5%Cu catalysts are 0.86 and 0.14, respectively. The $P_{Pt,observed} = 0.524$ and $P_{Cu,observed} = 0.039$ were calculated from the EXAFS fitting result (SI, part 4). Thus, $J_{Pt} = 60\%$ and $J_{Cu} = 28\%$. J_{Pt} and J_{Cu} values are smaller than 100%, which implies both Pt and Cu atoms were not preferred to be alloyed. The homoatomic Pt-Pt or Cu-Cu bonds are favoured over the heteroatomic Pt-Cu bonds. As $N_{Pt-M} \geq N_{Cu-M}$ the Pt particles were in the core and the Cu particles were in the shell.

6. Size distribution result by SAXS

Figure S2. The size distribution results obtained from SAXS.

7. Size distribution result from TEM images

Figure S3. (a, b) TEM picture of the Pt-Cu catalyst. (c) Size distribution histogram calculated from TEM images.

Reference

1. Ilavsky, J.; Jemian, P. R. *J Appl Crystallogr* **2009**, 42, 347-353.
2. Ghodselahi, T.; Vesaghi, M. A.; Shafiekhani, A.; Baghizadeh, A.; Lameii, M. *Appl Surf Sci* **2008**, 255, (5), 2730-2734.