Supporting Information for
Layered $\text{Na}_x\text{Cr}_x\text{Ti}_{1-x}\text{O}_2$ as Bi-Functional Electrode Materials
for Rechargeable Sodium Batteries

Yuka Tsuchiya¹, Kazuki Takanashi,¹ Takuya Nishinobo,¹ Akiko Hokura,¹ Masao Yonemura,^{2, 3}

Takeshi Matsukawa,⁴ Toru Ishigaki,⁴ Keisuke Yamanaka,⁵ Toshiaki Ohta⁵, and Naoaki

Yabuuchi^{1, 6*}

1) Department of Green and Sustainable Chemistry, Tokyo Denki University

5 Senju Asahi-Cho, Adachi, Tokyo 120-8551, Japan

2) Institute of Materials Structure Science (IMSS),

High Energy Accelerator Research Organization (KEK)

1-1 Oho, Tsukuba, Ibaraki 305-0801, Japan

3) Department of Materials Structure Science,

Sokendai (The Graduate University for Advanced Studies),

203-1 Shirakata, Tokai, Ibaraki 319-1106, Japan

4) Frontier Research Center for Applied Atomic Sciences, Ibaraki University

162-1 Shirakata, Tokai, Naka, Ibaraki 319-1106, Japan

5) SR Center, Ritsumeikan University, 1-1-1 Noji-Higashi, Kusatsu, Shiga 525-8577, Japan

6) Elements Strategy Initiative for Catalysts and Batteries, Kyoto University,

1-30 Goryo-Ohara, Nishikyo-ku, Kyoto 615-8245, Japan

*E-mail: yabuuchi@mail.dendai.ac.jp

Table S1. Summary of refined structural parameters by Rietveld analysis for the neutron diffraction patterns; (a) $x = 1.0$, (b) $x = 0.8$, and (c) $x = 0.67$ in $\text{Na}_x\text{Cr}_x\text{Ti}_{1-x}\text{O}_2$ samples.

(a) $x = 1$, O3 NaCrO_2

Atom	site	g	x	y	z	$B(\text{\AA}^2)$
Na(1)	3b	1	0	0	1/2	0.782(6) ^a
Cr(1)	3a	1	0	0	0	0.355(6) ^a
O(1)	6c	1	0	0	0.267489(10)	0.364(3) ^a

Atom	$U_{11}(\text{\AA}^2)$	$U_{22}(\text{\AA}^2)$	$U_{33}(\text{\AA}^2)$	$U_{12}(\text{\AA}^2)$	$U_{13}(\text{\AA}^2)$	$U_{23}(\text{\AA}^2)$
Na(1)	0.01059(12)	$= U_{11}(\text{Na(1)})$	0.0085(2)	$= U_{11}(\text{Na(1)})/2$	0	0
Cr(1)	0.00398(10)	$= U_{11}(\text{Cr(1)})$	0.00551(17)	$= U_{11}(\text{Cr(1)})/2$	0	0
O(1)	0.00438(5)	$= U_{11}(\text{O(1)})$	0.00505(7)	$= U_{11}(\text{O(1)})/2$	0	0

Space group $R\bar{3}m$ (No. 166, Hexagonal), $a = b = 2.977106(8)$ $\text{\AA}$, $c = 15.97758(7)$ $\text{\AA}$
 $R_{\text{wp}} = 4.99$, $R_p = 3.76$, $S = R_{\text{wp}}/R_e = 1.86$, $R_B = 2.27$, $R_F = 2.78$.

^a Equivalent isotropic thermal parameter, B_{eq} .

(b) $x = 0.80$, O3 $\text{Na}_{0.8}\text{Cr}_{0.8}\text{Ti}_{0.2}\text{O}_2$

Atom	site	g	x	y	z	$B(\text{\AA}^2)$
Na(1)	3b	0.8035(12)	0	0	1/2	0.654(14) ^a
Cr(1)	3a	0.8022(6)	0	0	0	0.219(14) ^a
Ti(1)	3a	0.1978(6)	0	0	0	$= B(\text{Cr(1)})^a$
O(1)	6c	1	0	0	0.229954(11)	0.692(6) ^a

Atom	$U_{11}(\text{\AA}^2)$	$U_{22}(\text{\AA}^2)$	$U_{33}(\text{\AA}^2)$	$U_{12}(\text{\AA}^2)$	$U_{13}(\text{\AA}^2)$	$U_{23}(\text{\AA}^2)$
Na(1)	0.0089(2)	$= U_{11}(\text{Na(1)})$	0.0071(3)	$= U_{11}(\text{Na(1)})/2$	0	0
Cr(1)	0.0025(2)	$= U_{11}(\text{Cr(1)})$	0.0033(4)	$= U_{11}(\text{Cr(1)})/2$	0	0
Ti(1)	$= U_{11}(\text{Cr(1)})$	$= U_{22}(\text{Cr(1)})$	$= U_{33}(\text{Cr(1)})$	$= U_{12}(\text{Cr(1)})$	0	0
O(1)	0.00940(10)	$= U_{11}(\text{O(1)})$	0.00751(11)	$= U_{11}(\text{O(1)})/2$	0	0

Space group $R\bar{3}m$ (No. 166, Hexagonal), $a = b = 2.962623(8)$ $\text{\AA}$, $c = 16.30695(16)$ $\text{\AA}$
 $R_{\text{wp}} = 13.37$, $R_p = 10.97$, $S = R_{\text{wp}}/R_e = 8.79$, $R_B = 11.62$, $R_F = 19.17$.

^a Equivalent isotropic thermal parameter, B_{eq} .

(c) $x = 0.67$, P2 $\text{Na}_{2/3}\text{Cr}_{2/3}\text{Ti}_{1/3}\text{O}_2$

Table 3: Rietveld refinement results for the sample ($x = 2/3$, P2- $\text{Na}_{2/3}(\text{Cr}_{2/3}\text{Ti}_{1/3})\text{O}_2$).

Atom	site	g	x	y	z	$B(\text{\AA}^2)$
Na(1)	2b	$= 2/3-g(\text{Na(2)})$	0	0	1/4	2.789(18) ^a
Na(2)	2d	0.4938(6)	1/3	2/3	3/4	$= B(\text{Na(1)})^a$
Cr(1)	2a	2/3	0	0	0	1.313(19) ^a
Ti(1)	2a	1/3	0	0	0	$= B(\text{Cr(1)})^a$
O(1)	4f	1	1/3	2/3	0.09275	0.604177(3) ^a

Atom	$U_{11}(\text{\AA}^2)$	$U_{22}(\text{\AA}^2)$	$U_{33}(\text{\AA}^2)$	$U_{12}(\text{\AA}^2)$	$U_{13}(\text{\AA}^2)$	$U_{23}(\text{\AA}^2)$
Na(1)	0.0500(3)	$= U_{11}(\text{Na(1)})$	0.0060(4)	$= U_{11}(\text{Na(1)})/2$	0	0
Na(2)	$= U_{11}(\text{Na(1)})$	$= U_{22}(\text{Na(1)})$	$= U_{33}(\text{Na(1)})$	$= U_{12}(\text{Na(1)})$	0	0
Cr(1)	0.0006(3)	$= U_{11}(\text{Cr(1)})$	0.0487(8)	$= U_{11}(\text{Cr(1)})/2$	0	0
Ti(1)	$= U_{11}(\text{Cr(1)})$	$= U_{22}(\text{Cr(1)})$	$= U_{33}(\text{Cr(1)})$	$= U_{12}(\text{Cr(1)})$	0	0
O(1)	0.00542121(3)	$= U_{11}(\text{O(1)})$	0.01211356(10)	$= U_{11}(\text{O(1)})/2$	0	0

Space group $P6_3/mmc$ (No. 194), $a = 2.941212(9)$ $\text{\AA}$, $c = 11.18307(5)$ $\text{\AA}$
 $R_{\text{wp}} = 4.07$, $R_p = 3.52$, $S = R_{\text{wp}}/R_e = 1.85$, $R_B = 2.22$, $R_F = 4.50$.

^a Equivalent isotropic thermal parameter, B_{eq} .

Figure S1. Results of Rietveld analysis of O3-NaCrO₂ and P2-Na_{2/3}Cr_{2/3}Ti_{1/3}O₂. Relatively large R_{wp} for P2-Na_{2/3}Cr_{2/3}Ti_{1/3}O₂ originates from the presence of stacking faults (see reference, N. Yabuuchi, M. Kajiyama, J. Iwatate, H. Nishikawa, S. Hitomi, R. Okuyama, R. Usui, Y. Yamada and S. Komaba, *Nature Materials*, **11**, 512 (2012).).

(a) Positive electrode

(b) Negative electrode

Figure S2. Reversible capacity retention of $\text{P2-Na}_{2/3}\text{Cr}_{2/3}\text{Ti}_{1/3}\text{O}_2$ at a rate of 10 mA g^{-1} .

(a) Positive electrode

(b) Negative electrode

Figure S3. Coulombic efficiency of $\text{Na}_x\text{Cr}_x\text{Ti}_{1-x}\text{O}_2$ samples at a rate of 10 mA g^{-1} at 25°C .

Figure S4. (a) Charge/discharge curves of acetylene black (HS-100) used in this study at a rate of 10 mA g⁻¹. Large irreversible capacity is noted for initial cycle.