Supporting Information

J. Am. Chem. Soc. **2011**, *113*(7), 2092–2095; DOI: [10.1021/ja1105078](https://doi.org/10.1021/ja1105078)

Mechanistic Insight into the Brust–Schiffrin two-phase synthesis of chalcogenate-protected metal nanoparticles

Ying Li, Oksana Zaluzhna, Bolian Xu, Guan Gao, Jacob M. Modest, YuYe J. Tong*

Department of Chemistry, Georgetown University, 37th and “O” Streets NW,
Washington D.C. 20057

*Email: yyt@georgetown.edu

Synthesis and Preparation

Dialkyl disulfide was synthesized according to a modified literature approach.¹ 15 mg NaI was added to the solution of 2.4-mL C₁₂H₂₅SH and 30-mL ethyl acetate. After the addition of 1.1 mL of 30 wt% H₂O₂, the mixture was stirred at room temperature for 30min, which led to a clear yellowish solution. 15-mL Na₂S₂O₃ (3.13 g) aqueous solution was then poured in. The color of the solution then faded. The two-phase mixture was transferred to a separatory funnel. After removing the solvent from the top solution, the desired product was obtained as white crystal powder.

[TOA][AuBr₄] was prepared following the reported approach.^{2,3} TOAB (1.26 g) and KAuBr₄·H₂O (1.37 g) were mixed with 60 mL of anhydrous EtOH. After 1-h stir and 10-min sonication, the mixture was stored in a freezer overnight. The expected product was collected through vacuum filtration.

[TOA][AuBr₂] was synthesized according to a revised literature approach.^{2,3} The mixture of [TOA][AuBr₄] (0.88 g) and 8.8-mL anhydrous EtOH was heated in water bath up to 70°C, by which [TOA][AuBr₄] was completely dissolved in EtOH. Once the temperature of water bath reached 70°C, 0.88-mL acetone was added. After that, the solution turned to white cloudy in a short time and then heating was stopped. When the mixture was cooled down, vacuum filtration was performed to remove the white insoluble byproduct. The clear colorless filtrate was stored in a freezer overnight. The expected product was collected through vacuum filtration as colorless crystals.

[MSR]_n polymer was prepared directly following the reported approach.⁴ 0.1mmole metal salt (i.e. HAuCl₄, AgNO₃, and CuCl₂·H₂O) was dissolved in 1.0 mL H₂O, then mixed with 20-mL THF, and 0.10-mL C12SH was added. After an overnight stir, the

precipitate, which was the desired product, was collected with vacuum filtration.

Dodecanethiol self-assembled on rough Au electrode. A commercial gold rod electrode (Bioanalytical, 2 mm²) was used. The Au electrode was first roughened by square wave oxidation–reduction cycles (SWORC) method devised by Dr. Bolian Xu in our group. In details, the Au electrode was subject to square wave cycling that had a frequency of 166 Hz and upper and lower switching potentials at 2.4 V and –0.2 V respectively in a supporting electrolyte of 0.5 M H₂SO₄ for 30 min. The electrode was held at +1.4V and then -0.25 V for 5~10 min respectively until a decay curve was observed in the Raman spectra of the electrode surface after holding at -0.25V. The clean rough Au electrode was immersed into 1 mL of 10 mM C₁₂H₂₅SH EtOH solution overnight, and then rinsed with EtOH.

Diocetyl diselenide was synthesized directly following the previously reported work of our group⁵ with the additional purification step, where the silica/hexanes column (60 cm in length and 6 cm in diameter) was run to purify the product.

Didodecyl ditelluride was synthesized directly following the route in our previous paper.⁶ Here C₁₂H₂₅Br was used to replace C₈H₁₇Br. Since (C₁₂H₂₅Te)₂ was solid, the purification steps aiming to remove the liquid C₁₂H₂₅Br were not necessary to be followed.

Typical synthesis of chalcogenate Au Nanoparticles. (1) Brust-Schiffrin two-phase method: 0.70 mL of 0.1421M HAuCl₄ (0.10 mmole) aqueous solution was mixed with 10 mL of TOAB (0.30 mmole) toluene solution. After 30-min vigorous stirring, the top wine-red solution was collected and then the ligands (0.30 mmole C₁₂H₂₅SH, 0.05 mmole disulfide, 0.05 mmole (C₈H₁₇Se)₂, or 0.034 mmole (C₁₂H₂₅Te)₂) were added dropwise. After stirring for 1h, 1 mL of fresh NaBH₄ (1 mmole) aqueous solution was poured in. The mixture was stirred overnight and then transferred to separatory funnel. The organic phase was rinsed with water three times and was put through vacuum filtration. After the removal of most solvent by rotary evaporation with pump, ~50 mL of EtOH (for S-contained ligands) or acetonitrile (for Se- and Te-contained ligands) was added to black slurry. The mixture was sonicated for couple of minutes and then stored in a freezer overnight. The desired product was the filter cake after filtering with microfilter system. In order to get narrow size distribution, centrifugation (14.5k rpm for 1 hour) could be taken. (2) Our reversed synthetic route: 0.70 mL of 0.1421M HAuCl₄ (0.10 mmole) aqueous solution was mixed with 10 mL of TOAB (0.30 mmole) toluene solution. After 30-min vigorous

stirring, 1 mL of fresh NaBH_4 (1 mmole) aqueous solution was added. In around 10 second or shorter time, the ligands dissolved in 1~2 mL of toluene (0.30 mmole $\text{C}_{12}\text{H}_{25}\text{SH}$, 0.05 mmole disulfide, 0.05 mmole $(\text{C}_8\text{H}_{17}\text{Se})_2$, or 0.05 mmole $(\text{C}_{12}\text{H}_{25}\text{Te})_2$) were poured in. After stirring for some time (overnight for S-contained ligands, 1 hour for diselenide, and 10 min for ditelluride), the solution was measured with UV-vis spectroscopy. The nanoparticles could be collected following the same procedures mentioned above.

Typical synthesis of alkanethiolate Ag Nanoparticles. The same recipes were used as those for Au nanoparticles, except the procedures for the phase transfer of Ag cation and the ratio of thiol to Ag (i.e. S:Ag = 1.5:1). The following procedures were used to make all of Ag^+ transfer from aqueous to organic phase. 0.1mmole AgNO_3 was dissolved in ~5 mL water and then mixed with 10 mL of TOAB (0.3 mmole) toluene solution. The mixture was stirred vigorously overnight or longer until all precipitate disappeared and a clear colorless two-layer solution was obtained.

Typical synthesis of alkanethiolate Cu Nanoparticles. Because of the low efficiency of phase transfer of Cu cation via the traditional method which was used for Au and Ag ions⁷, a reported approach^{3,8} was followed. $\text{CuCl}_2 \cdot \text{H}_2\text{O}$ (0.1 mmole) and TOAB (0.2 mmole) were mixed in 50-mL anhydrous ethanol. The mixture was heated in water bath to 80°C. After 30-min stirring at 80°C, the solvent was removed from the clear dark red solution by rotary evaporation with pump. The obtained dark red solid, $[\text{TOA}]_2[\text{CuX}_4]$, was used as the Cu source of the synthesis. The same procedures except the phase transfer as those used for Au and Ag nanoparticles were followed.

Characterization

Raman spectroscopy. The spectra were obtained using a confocal microprobe Raman system (Renishaw RM1000) equipped with a deep depletions CCD peltier cooled down to -70 °C . The microscope attachment was based on an Olympus BH2-UMA system and a 50x-long working-length objective (8 mm) was used. A holographic notch filter was used to filter the exciting line and two selective holographic gratings (1200 g/mm and 2400 g/mm) were employed with respect to the required spectral resolution. The exciting wavelength was 785 nm from a Renishaw Ar ion laser with a max power of 27 mW and a spot of ca. 3 μm on the surface. The slit and pinhole in experiment were 100 and 400 μm , respectively. The spectroscopy was calibrated with the peak at 520 cm^{-1} of clean Si wafer. Liquid sample was measured in 5-mm NMR tube. Solid or slurry sample was measured on clean microscope slide.

UV-vis spectroscopy. Solid samples were first dissolved in toluene to make a dilute solution. They were then transferred into a 1-cm path length quartz cuvette and the measurements were done on a HP 8453 diode array UV/Vis spectrometer. A typical experiment scanned the wavelength from 300 to 800 nm. Background adjustments were made using toluene as blank.

NMR. ^1H NMR spectra were recorded on a Bruker AM 300 MHz spectrometer that was interfaced with a Tecmag DSpect acquisition system. Deuterated benzene was used as a solvent, whose ^1H (7.16 ppm) and ^{13}C (128.39 ppm) peaks were used as references.

TEM. The TEM characterization was performed on JEOL JEM-2100 LaB₆ transmission electron microscope at 100 kV. The samples were prepared by placing two or three drops of the dilute nanoparticle dispersion in toluene on carbon-coated copper grids (400 mesh, Electron Microscopy Science). Nanoparticle sizes were measured using ImageJ.

DLS. Dynamic light scattering (DLS) was performed using a 632.8nm HeNe laser excitation and a single mode optical fiber collection, which is coupled to an avalanche photodiode detector (Perkin Elmer SPCM CD22882). The collected signals were input to and analyzed by an ALV-5000 Multiple Tau Digital Correlator software.

Figure S1. ^1H NMR spectra of (a) the intermediate obtained after the addition of 2 equiv of dodecanethiol to TOAB-plus-Au(III) (TOAB: Au = 3:1) C_6D_6 layer, (b) synthesized $[\text{TOA}][\text{AuBr}_2]$ complex, (c) TOAB, (d) dodecanethiol, and (e) synthesized didodecyl disulfide, all in 0.80 mL C_6D_6 .

Figure S2. Raman spectra of (a) dodecanethiol, (b) didodecyl disulfide, (c) synthesized $[\text{AgSR}]_n$ polymer, (d) the mixture of AgNO_3 aqueous solution and 3 equiv of TOAB toluene after removing most solvent, (e) adding 3 equiv of dodecanethiol to the benzene layer of AgNO_3 and 3 equiv of TOAB and removing most solvent, and (f) TOAB.

Figure S3. Raman spectra of (a) dodecanethiol, (b) didodecyl disulfide, (c) synthesized $[\text{CuSR}]_n$ polymer, (d) synthesized $[\text{TOA}]_2[\text{CuX}_4]$, (e) the mixture of $[\text{TOA}]_2[\text{CuX}_4]$ and 3 equiv of dodecanethiol in toluene after removal of most solvent, (f) $\text{CuCl}_2 \cdot \text{H}_2\text{O}$, (g) CuBr , and (h) TOAB. (X: Cl or Br)

Figure S4. DLS spectra of (a) the toluene layer of HAuCl_4 and 3 equiv of TOAB, (b) the clear colorless solution obtained after adding 2 equiv of octanethiol to the toluene layer of HAuCl_4 and 3 equiv of TOAB.

Figure S5. TEM image of dodecanethiolate-protected gold nanoparticles (1.8 ± 0.4 nm) by Brust-Schiffrin two-phase method

Figure S6. TME images of dodecanethiolate-protected (a) Ag (2.9 ± 0.4 nm) and (b) Cu (1.8 ± 0.3 nm) nanoparticles by our reversed synthetic route.

Figure S7. UV-vis spectra of dodecanethiolate-protected (a) & (b) Au, (c) & (d) Ag, and (e) & (f) Cu nanoparticles by the Brust-Schiffrin two-phase method (dot line) vs. our reversed synthetic route (solid line).

Figure S8. UV-vis absorption spectra of dodecanethiolate-protected Au nanoparticles by our reversed synthetic route with (a) 1, (b) 2, (c) 3, (d) 0 equiv of dodecanethiol in toluene. The stirring time before adding thiols was 10s.

Figure S9. TEM images of dodecanethiolate-protected Au nanoparticles through our reversed synthetic route with (a) 1 (3.9 ± 0.6 nm), (b) 2 (2.5 ± 0.5 nm), (c) 3 (1.7 ± 0.3 nm), and (d) 0 (i.e. without any ligand, also named as “naked” TOA-stabilized Au nanoparticles, 5.30 ± 0.94 nm) equiv of dodecanethiol. The stirring time before adding thiols was 10s.

Figure S10. UV-vis spectra and TEM images of Au nanoparticles formed using didodecyl disulfide as ligands by (a) Brust-Schiffrin two-phase method (1.8 ± 0.3 nm) vs. (b) our reversed synthetic route (2.0 ± 0.3 nm).

Figure S11. ^1H NMR spectra of (a) TOAB, (b) dioctyl disulfide, (c) adding 3 equiv octanethiol to the organic phase of HAuCl_4 and 3 equiv of TOAB (i.e. $\text{HAuCl}_4 + 3\text{TOAB}$), (d) dioctyl diselenide, (e) adding 0.5 equiv dioctyl diselenide to $\text{HAuCl}_4 + 3\text{TOAB}$, (f) dioctyl ditelluride, and (g) adding 1/3 equiv dioctyl ditelluride to $\text{HAuCl}_4 + 3\text{TOAB}$ in C_6D_6 .

References

- (1) Kirihara, M.; Asai, Y.; Ogawa, S.; Noguchi, T.; Hatano, A.; Hirai, Y. *Synthesis* **2007**, 2007, 3286-3289.
- (2) Braunstein, P.; Clark, R. J. H. *Journal of the Chemical Society, Dalton Transactions* **1973**, 1845-1848.
- (3) Goulet, P. J. G.; Lennox, R. B. *Journal of the American Chemical Society* **2010**, 132, 9582-9584.
- (4) Kim, J.-U.; Cha, S.-H.; Shin, K.; Jho, J. Y.; Lee, J.-C. *Journal of the American Chemical Society* **2005**, 127, 9962-9963.
- (5) Deacon, M. L.; Zelakiewicz, B. S.; Tong, Y. Y. *Synlett* **2005**, 2005, 1618-1620.
- (6) Li, Y.; Silverton, L. C.; Haasch, R.; Tong, Y. Y. *Langmuir* **2008**, 24, 7048-7053.
- (7) Dadgostar, N.; Ferdous, S.; Henneke, D. *Mater Lett* **2010**, 64, 45-48.
- (8) Gill, N. S.; Taylor, F. B.; Hatfield, W. E.; Parker, W. E.; Fountain, C. S.; Bunger, F. L. *Inorg. Synth.* **1967**, 9, 136-142.