Supporting information

Multivalent targeting of AT₁ receptors with Angiotensin II-functionalized nanoparticles

Robert Hennig¹, Klaus Pollinger¹, Joerg Tessmar² and Achim Goepferich^{1*}

¹Department of Pharmaceutical Technology, University of Regensburg, Regensburg, Germany

²Department for Functional Materials in Medicine and Dentistry, University Hospital of
Wuerzburg, Wuerzburg, Germany

*Corresponding author:

Prof. Dr. A. Goepferich

Department of Pharmaceutical Technology

University of Regensburg,

Universitätsstr. 31, 93053 Regensburg, Germany

Telephone: 0049(0)941 943 4842

Fax: 0049(0)941 943 3807

E-mail: achim.goepferich@chemie.uni-regensburg.de

Transmission electron microscopy

3 μL of a 60 nM aqueous solution Qdots was pipetted on a carbon-coated copper grid (Plano, Wetzlar, Germany) and air dried. The sample was analyzed using a Zeiss Libra 120 electron microscope (Zeiss, Oberkochen, Germany). Electron microscopy pictures were acquired with Image SP (Zeiss, Oberkochen, Germany) and analyzed with ImageJ.

Figure S1: Transmission electron microscopy pictures of Qdots before and after conjugation. The conjugation process did not alter the dispersity and did not lead to Qdot aggregation.

PEGylation of Angiotensin II

2 μmol Angiotensin II was reacted with 4 μmol mPEG5k-succinimidyl carbonate for 16 hours at room temperature in borate buffer (50 mM, pH 8.5). mPEG5k-succinimidyl carbonate was synthesized as described in the literature [1]. The reaction mixture was purified by size exclusion chromatography using a Sephadex G-25 resin in a PD-10 column with DPBS as the eluent. Fractions containing PEGylated Ang II were pooled and further purified by ultrafiltration using a 5 KDa molecular weight cut-off Amicon Ultra-15 filter unit. Final purity and conjugate concentration were determined using RP18-HPLC: The HPLC system consisted of a Shimadzu LC-10ATVP pump (Shimadzu, Duisburg, Germany), a Shimadzu SIL-10ADVP autosampler

connected to a Shimadzu SPD-10A UV-Vis detector. A Luna[®] 5 μ m C18(2) 100 Å 250 x 4.60 mm LC column (Phenomenex, Aschaffenburg, Germany) was used as separation column. The peptides were analyzed based on a linear acetonitrile–trifluoroacetic acid (TFA)–water gradient with a flow rate of 1 mL/min. Elution was obtained by using the following gradient of solvents A (0.1 % (v/v) TFA in water) and B (0.1 % (v/v) TFA in acetonitrile): 75:25 (A:B) to 30:70 in 20 min and reequilibration to 90:10 in the following 7 min. The column was operated at 35 °C. The peptide and its PEG conjugate were detected at 275 nm. The affinity of the conjugate was measured with an intracellular calcium mobilization assay using fura-2AM.

Figure S2: PEGylation of Angiotensin II **(A)** RP18-HPLC analysis of Ang II and its PEGylated counterpart showing the absence of unreacted Ang II. **(B)** Upon PEGylation, the peptide's affinity dropped 4.5-fold to 320 ± 42 nM

References

- [1] F. Brandl, N. Hammer, T. Blunk, J. Tessmar, A. Goepferich, Biodegradable hydrogels for time-controlled release of tethered peptides or proteins, *Biomacromolecules* 11 (2010) 496–504.