Supporting Information

Surface Plasmon Resonance Near-Infrared Spectroscopy

Akifumi IKEHATA, Tamitake ITOH, and Yukihiro OZAKI*

Department of Chemistry and Research Center for Near Infrared Spectroscopy,
School of Science and Technology, Kwansei Gakuin University,
2-1 Gakuen, Sanda 669-1337, Japan

*Corresponding author: ozaki@ksc.kwansei.ac.jp

Table S1: Table S1: Coefficients of Sellmeier Equation (2) for BK7 and LaSF15N.

material	α	β	γ	δ
BK7	2.2741	0.010060	0.017203	-0.010723
LaSF15	3.4188	0.036029	0.028208	-0.016197

Figure S1: Process flowchart of the spectral acquisition.

Figure S2: SPR-NIR spectra in the 8000–4000 cm⁻¹ region of water (left panels) and ethanol (right panels) on the gold films with the different thickness (L1~L5) on the LaSF15 prism. The spectra were measured over an incident angle range of 43.5° to 50.0° for water and of 46.0° to 50.0° for ethanol. The data are shown with an increment of 0.2°. The dashed lines represent ATR spectra measured at $\theta = 51.0^\circ$. The insets show enlarged ATR spectra (the 6000–4500 cm⁻¹ region for water and the 5500–4100 cm⁻¹ region for ethanol).

Figure S3: Calculated SPR-NIR spectra of water for BK7 (left panels) and LaSF15 (right panels) under the same conditions of the thickness of gold film as the experiment. The calculations were carried out by the convolution with the angular distribution (FWHM=0.5°). The dotted lines denote calculated ATR spectra of water and their enlarged spectra are shown in the insets.