Synthesis of copper-decorated CeO₂ catalysts.

Matías Jobbágy,^{1,*} Fernando Mariño², Betina Schonbröd², Graciela Baronetti², Miguel Laborde²

¹INQUIMAE, Facultad de Ciencias Exactas y Naturales, Universidad de Buenos Aires, Pabellón II, Ciudad Universitaria, C1428EHA - Buenos Aires, Argentina.

²Laboratorio de Procesos Catalíticos, Facultad de Ingeniería, Universidad de Buenos Aires, Pabellón de Industrias, Ciudad Universitaria, C1428EHA - Buenos Aires, Argentina.

Corresponding author E-mail: jobbag@qi.fcen.uba.ar

Supporting Information

Figure 1. SEM micrographs of sample CeCu20 (**A**), CeCu30 (**B**), CeCu40 (**C**) and CeCu60 (**D**). aged at 363 K for 5 h. Scale bar = 5 μm .

Figure 2. TG curves of samples CeCu20 (**A**), CeCu30 (**B**), CeCu40 (**C**) aged at 363 K for 5 h., decomposed at 3 K min.⁻¹ in air flow (20 mL min.⁻¹).

Figure 3. PXRD patterns of samples CeCu20 (**A**), CeCu30 (**B**), CeCu40 (**C**), CeCu50 (**D**) and CeCu60 (**E**) aged at 363 K for 5 h. Asterisks denotes the presence of Cu(II) basic salts.

Figure 4. PXRD patterns of samples CeCu10 (**A**), CeCu20 (**B**), CeCu30 (**C**), CeCu40 (**D**), CeCu50 (**E**) and CeCu60 (**F**) decomposed in air (20 mL min^{-1}) at 3 K min^{-1} , holding the final temperature of 873 K for 30 min. Asterisks denotes the presence of Tenorite (CuO).

Figure 5. CO conversion as a function of reaction temperature and catalyst composition. Mass of catalyst: 200 mg. Total inlet flow rate 230 mL min^{-1} . Feed composition: 89.5% H_2 , 2.3% CO, 1.7% O_2 ($\lambda = 1.5$), N_2 balance (6.5%).