Supplementary Information

Thermotropic Liquid-Crystalline Properties of 4,4'-Dialkoxy-3,3'-diaminobiphenyl Compounds and Their Precursors

Pradip K. Bhowmik,^a Shane T. Killarney,^a Jung Jae Koh,^a Ontida Tanthmanatham^a and Haesook Han^a

^aDepartment of Chemistry and Biochemistry, University of Nevada Las Vegas, 4505 S. Maryland Parkway, Box 454003, Las Vegas, NV 89154, USA

E-mail: pradip.bhowmik@unlv.edu

Tyler Harris,^b Michael R. Fisch,^c Deña M. Agra-Kooijman,^b Lewis Sharpnack^b and Satyendra Kumar^b

^bDepartment of Physics and ^cCollege of Applied Engineering, Sustainability and Technology, Kent State University, Kent, OH 44242, USA

List of Contents

Figure S1. DSC thermograms (a) of **DN1** and (b) of **DA1** obtained at heating and cooling rates of 10 °C/min in nitrogen. p 3

Figure S2. DSC thermograms (a) of **DN2** and (b) of **DA2** obtained at heating and cooling rates of 10 °C/min in nitrogen. p 4

Figure S3. X-ray diffraction patterns (a-c) of **DN2** showed only a transition from isotropic (95.6 °C) to crystal (94.3 °C) and crystalline phase (90.1 °C). This is confirmed by optical textures (d-f). p 5

Figure S4. X-ray diffraction patterns (a-b) of **DA3** that represent SmA phase (d-spacings: 25.2 Å, 12.6 Å, ~ 6.2 Å (weak, diffused), and ~ 4.7 Å)) and (c) of **DA3** represents the crystalline phase (taken on cooling from the isotropic phase). The d-spacings were determined the peak positions indicated in their corresponding intensity vs. q profile (d-e). p 6

Figure S5. DSC thermograms (a) of **DN4** and (b) of **DA4** obtained at heating and cooling rates of 10 °C/min in nitrogen. p 7

Figure S6 DSC thermograms (a) of **DN5** and (b) of **DA5** obtained at heating and cooling rates of 10 °C/min in nitrogen. p 8

Figure S7. X-ray diffraction pattern (a-b) of **DN5** that display SmA phase and the crystalline phase, and optical textures (c-d) display its SmA phase and crystalline phase, respectively (taken on cooling from the isotropic phase). p 9

Figure S8. DSC thermograms (a) of **DN6** and (b) of **DA6** obtained at heating and cooling rates of 10 °C/min in nitrogen. p 10

Figure S9. X-ray diffraction pattern (a-b) of **DN6** that display SmA phase and the crystalline phase, and optical textures (c-d) display its SmA phase and crystalline phase, respectively (taken on cooling from the isotropic phase). p 11

Figure S10. X-ray diffraction pattern (a-b) of **DA6** that display SmA phase and the crystalline phase, and optical textures (c-d) display its SmA phase and crystalline phase, respectively (taken on cooling from the isotropic phase). p 12

Figure S11. DSC thermograms (a) of **DN7** and (b) of **DA7** obtained at heating and cooling rates of 10 °C/min in nitrogen. p 13

Figure S12. X-ray diffraction pattern (a-b) of **DN7** that display SmA phase and the crystalline phase, and optical textures (c-d) displaying its SmA phase and crystalline phase, respectively (taken on cooling from the isotropic phase). p 14

Figure S13. X-ray diffraction patterns (a-c) of **DA7** indicate SmA phase at 100 and 70 °C and crystalline phase at 60 °C and associated optical textures (d-f), displaying SmA at 105, 70.0 and crystalline phase at 61.7 °C, respectively (taken on cooling from the isotropic phase). p 15

Figure S14. DSC thermograms (a) of **DN8** and (b) of **DA8** obtained at heating and cooling rates of 10 °C/min in nitrogen. p 16

Figure S15. DSC thermograms of **DN9** obtained at heating and cooling rates of 10 °C/min in nitrogen. p 17

Figure S16. X-ray diffraction patterns (a-b) of **DN9** indicate crystalline phase at 30 °C, isotropic phase at 59.3 °C, and (c) optical texture displaying crystalline phase at 56.2 °C, respectively (taken on cooling from the isotropic phase). p 18

(a)

(b)

Figure S1. DSC thermograms (a) of **DN1** and (b) of **DA1** obtained at heating and cooling rates of 10 °C/min in nitrogen.

(a)

(b)

Figure S2. DSC thermograms (a) of **DN2** and (b) of **DA2** obtained at heating and cooling rates of 10 °C/min in nitrogen.

Figure S3. X-ray diffraction patterns (a-c) of **DN2** showed only a transition from isotropic (95.6 °C) to crystal (94.3 °C) and crystalline phase (90.1 °C). This is confirmed by optical textures (d-f).

Figure S4. X-ray diffraction patterns (a-b) of **DA3** that represent SmA phase (d-spacings: 25.2 Å, 12.6 Å, ~ 6.2 Å (weak, diffused), and ~ 4.7 Å)) and (c) of **DA3** represents the crystalline phase (taken on cooling from the isotropic phase). The d-spacings were determined the peak positions indicated in their corresponding intensity vs. q profile (d-e).

(a)

(b)

Figure S5. DSC thermograms (a) of **DN4** and (b) of **DA4** obtained at heating and cooling rates of 10 °C/min in nitrogen.

(a)

(b)

Figure S6. DSC thermograms (a) of **DN5** and (b) of **DA5** obtained at heating and cooling rates of 10 °C/min in nitrogen.

Figure S7. X-ray diffraction pattern (a-b) of **DN5** that display SmA phase and the crystalline phase, and optical textures (c-d) display its SmA phase and crystalline phase, respectively (taken on cooling from the isotropic phase).

(a)

(b)

Figure S8. DSC thermograms (a) of **DN6** and (b) of **DA6** obtained at heating and cooling rates of 10 °C/min in nitrogen.

Figure S9. X-ray diffraction pattern (a-b) of **DN6** that display SmA phase and the crystalline phase, and optical textures (c-d) display its SmA phase and crystalline phase, respectively (taken on cooling from the isotropic phase).

Figure S10. X-ray diffraction pattern (a-b) of **DA6** that display SmA phase and the crystalline phase, and optical textures (c-d) display its SmA phase and crystalline phase, respectively (taken on cooling from the isotropic phase).

(a)

(b)

Figure S11. DSC thermograms (a) of **DN7** and (b) of **DA7** obtained at heating and cooling rates of 10 °C/min in nitrogen.

Figure S12. X-ray diffraction pattern (a-b) of **DN7** that display SmA phase and the crystalline phase, and optical textures (c-d) displaying its SmA phase and crystalline phase, respectively (taken on cooling from the isotropic phase).

Figure S13. X-ray diffraction patterns (a-c) of **DA7** indicate SmA phase at 100 and 70 °C and crystalline phase at 60 °C and associated optical textures (d-f), displaying SmA at 105, 70.0 and crystalline phase at 61.7 °C, respectively (taken on cooling from the isotropic phase).

(a)

(b)

Figure S14. DSC thermograms (a) of **DN8** and (b) of **DA8** obtained at heating and cooling rates of 10 °C/min in nitrogen.

Figure S15. DSC thermograms of **DN9** obtained at heating and cooling rates of 10 °C/min in nitrogen.

Figure S16. X-ray diffraction patterns (a-b) of **DN9** indicate crystalline phase at 30 °C, isotropic phase at 59.3 °C, and (c) optical texture displaying crystalline phase at 56.2 °C, respectively (taken on cooling from the isotropic phase).