This item was submitted to [Loughborough's Research Repository](#) by the author.
Items in Figshare are protected by copyright, with all rights reserved, unless otherwise indicated.

UHTC composites for hypersonic applications

PLEASE CITE THE PUBLISHED VERSION

PUBLISHER

© The American Ceramic Society

VERSION

VoR (Version of Record)

LICENCE

CC BY-NC-ND 4.0

REPOSITORY RECORD

Paul, Anish, Daniel Doni Jayaseelan, Saranya Venugopal, E. Zapata-Solvas, J.G.P. Binner, Bala Vaidhyanathan, A. Heaton, Peter M. Brown, and W.E. Lee. 2012. "UHTC Composites for Hypersonic Applications". figshare. <https://hdl.handle.net/2134/9676>.

This item was submitted to Loughborough's Institutional Repository (<https://dspace.lboro.ac.uk/>) by the author and is made available under the following Creative Commons Licence conditions.

For the full text of this licence, please go to:
<http://creativecommons.org/licenses/by-nc-nd/2.5/>

Credit: DARPA artist's concept

◀ Figure 1 USAF Falcon Hypersonic Space Vehicle.

A. Paul, D.D. Jayaseelan,
S. Venugopal, E. Zapata-Solvas,
J. Binner, B. Vaidhyanathan,
A. Heaton, P. Brown and W.E. Lee

bulletin cover story

UHTC composites for hypersonic applications

Refractory non-oxides protect leading edges
of hypersonic vehicles during flight.

A dream for many scientists, engineers and sci-fi enthusiasts is of an aerospace vehicle that can take off from an airport, fly through the atmosphere and travel to the other side of the earth at hypersonic speeds, and then return through the atmosphere to the same or another airport. Thanks to programs like DARPA's Falcon Hypersonic Technology Vehicle 2 program (Figure 1), the dream is taking form.

Hypersonic vehicles need sharp leading edges to enable vehicle manoeuvrability during atmosphere exit and re-entry. The edges will see temperatures well in excess of 2000°C and be hit with corrosive plasmas from the atmosphere at ablative speeds. Other challenges associated with these conditions include severe oxida-

tion, extreme heat fluxes and high mechanical stresses.¹ Components, such as the leading edges, combustors and thermal protection systems, thus require materials that can withstand the high thermal, mechanical and shock-wave loadings that these aircraft will experience during flight. Such demanding requirements limit the field of possible materials to ultra-high-temperature ceramics. These are typically non-oxides with melting/decomposition temperatures in excess of 3000°C. Examples include borides, nitrides and carbides of Group IV-V metals in the periodic table, such as ZrB_2 , HfB_2 , ZrC , HfC , TaC and HfN .^{2,3}

Development of non-oxide ceramics has lagged behind that of oxides because they are rarely found in nature, need to be processed in controlled reducing atmospheres and tend to oxidize in air even at room temperature, especially when in fine powder form. As a result, the understanding of their crystal chemistry and the processing–microstructure–property relations is nowhere near that of, for example, simple oxides, silicates, phosphates and complex oxide systems. Fulfilling this dream will require a revolution in aviation with a key challenge being the vehicle thermal protection

Figure 2 Microstructure of ZrB_2 -5-volume-percent SiC composite.

system in which UHTCs will have a crucial role.

Early work on UHTCs

Bulk single-phase UHTCs for these high-temperature structural applications are limited by their poor oxidation and ablation resistance as well as poor damage tolerance.^{4–7} Research efforts have focused on improving the oxidation and thermomechanical properties, but such studies need to expand the boundaries of property measurement capability because the service temperatures and heat fluxes are so high. Various densification routes, including hot pressing, pressureless sintering, self-propagating high-temperature synthesis, reactive hot pressing and spark-plasma sintering,⁸ have been investigated to optimize fabrication procedures and performance of UHTCs.

Development of composite UHTC systems has focused on particulate additions, particularly of SiC at approximately 20 volume percent, because it significantly improves oxidation resistance at temperatures up to 1500°C by forming a protective amorphous, liquid borosilicate coating.⁹ There have been many previous attempts to improve the oxidation resistance of ZrB_2 – HfB_2 ceramics by, for example, increasing the viscosity of the liquid silica layer, increasing the immiscibility of different liquid phases or by developing dense ZrO_2 layers via liquid-phase sintering to reduce oxygen penetration and diffusivity.⁸ However, in hypersonic applications, the temperature often exceeds 2000°C in combination with severe air-flow. In such extreme conditions, any molten liquid will be blown off, rapidly exposing the underlying layer leading to further oxidation and UHTC recession.

UHTC development: Chemistry, processing and properties

Initial research at Imperial College, London aimed to develop solid refractory oxide protective layers by adding rare-earth borides or oxides to a baseline ZrB_2 –20-volume-percent-SiC (known as ZS20) UHTC.¹⁰ However, it is clear that if satisfactory thermal protection performance is to be achieved

in the severe conditions encountered, innovative and step-changing approaches are needed. A collaborative UK program between Loughborough University

and Imperial College is attempting to find some of these approaches.

The work at Imperial has focused on processing dense monolithic UHTC systems using SPS and measuring properties at increasingly high temperatures, while that at Loughborough has been aimed at incorporating UHTC powders into carbon-fiber preforms and evaluating the high-temperature oxidation performance. Current work is focused on developing composite systems by joining the two systems together with concomitant protective oxide layer formation. The work is being undertaken in collaboration with the United States Air Force Research Laboratory's Materials and Manufacturing Directorate, whose UHTC research focuses on developing a physical model to understand the oxidation mechanisms of zirconium and hafnium diboride-based ceramics and on developing UHTC composites reinforced with silicon carbide fibers.¹¹

A series of fully dense ZrB_2 -, HfB_2 - and TaC-based UHTC composites has been fabricated using the SPS facility at Queen Mary University, London. Figure 2 shows a typical microstructure of a 5-volume-percent-SiC-reinforced ZrB_2 composite sintered at 1900°C, revealing a dense microstructure with no visible cracks or pores. The grey grains forming the matrix are ZrB_2 , the mean grain size is less than 5-micrometers, and the grains are faceted. The dark grains are SiC and they predomi-

Figure 3 SEM and TEM images of HS20–5-weight-percent- LaB_6 composite showing an even distribution of LaB_6 and SiC in the HfB_2 matrix.

Figure 4 Thermal diffusivity of ZrB_2 - and HfB_2 -based UHTCs versus temperature.

nantly occur as less than 1-micrometer intergranular inclusions.

HfB_2 -based ceramics are more difficult to densify and must be sintered at temperatures at least 100°C higher than their ZrB_2 counterparts. Figure 3 shows SEM and TEM images of HfB_2 –20-volume-percent-SiC–5-weight-percent- LaB_6 (HS20–5-weight-percent LaB_6) composites sintered at 2000°C.

Coefficients of thermal expansion measured from room temperature to 2000°C showed that monolithic ZrB_2 had the highest CTE with a value of $7.8 \times 10^{-6} \text{ K}^{-1}$. This was slightly higher than that of monolithic HfB_2 at $7.6 \times 10^{-6} \text{ K}^{-1}$. SiC and all other additions investigated reduced the CTE values below the values of the baseline UHTC matrices. For all UHTC composites, however, the CTE increased from $5.5 \times 10^{-6} \text{ K}^{-1}$ at 200°C to $7 \times 10^{-6} \text{ K}^{-1}$ at 2000°C. The relatively large CTE values for UHTCs compared with more traditional thermal protection materials, such as the silica-based tile (CTE of $4.2 \times 10^{-6} \text{ K}^{-1}$) used by the space shuttles, present a number of design

UHTC composites for hypersonic applications

Figure 5 Cross-section microstructures of (a) ZrB_2 , (b) ZS20 and (c) ZS20- LaB_6 oxidized for 1 hour at 1600°C .

Figure 6 Photographs of HfB_2 -based UHTCs tested for 60 seconds at 8.2 and 15.2 megawatts per square meter using a defocused Nd:YAG laser.

challenges. The large CTE makes the materials significantly less resistant to thermal shock and, hence, makes it difficult for designers, who need to account for the different CTEs of multipart components to prevent cracking caused by constrained expansion on heating.

Thermal diffusivities (Figure 4) were measured during heating using the laser flash diffusivity technique. ZrB_2 and HfB_2 had the highest diffusivity values, approximately 40 square millimeters per second, at room temperature, while their lowest values, 10 and 15 square millimeters per second, respectively, occurred at 1900°C , the highest temperature at which measurements were undertaken. Additions of SiC and La_2O_3 decreased the thermal diffusivity by at least 10 percent. A plausible explanation for this is the formation of microcracks between grains, as occurs in many polycrystalline materials manufactured by high-temperature sintering processes, where thermal expansion mismatch between adjacent grains can lead to stresses on cooling.

Microcracking is known to degrade thermal properties in ceramics, and

Monteverde¹² has documented debonding between HfB_2 and SiC grains as well as microcracked HfB_2 grains in reactive hot-pressed HfB_2 -22.1-volume-percent-SiC-5.9-volume-percent-HfC. A key observation is that while thermal conductivities of all UHTCs studied are significantly different at room temperature, they converge to similar values at high temperatures.¹³ This is convenient from a design

perspective because, independent of the UHTC used, all will perform in a similar manner at the working temperatures.

Figure 5 shows cross-section microstructures of ZrB_2 , ZS20 and ZS20- LaB_6 . In-situ oxidation-resistant, refractory coatings have been generated on various UHTCs densified using SPS and containing rare-earth additives, such as LaB_6 , La_2O_3 and Gd_2O_3 . Oxidation of ZS20- LaB_6 for 1 hour at 1600°C in static air led to formation of a dense surface layer, up to 250 micrometers thick, of ZrO_2 and rare-earth zirconates. With melting points well above 1600°C , both phases remained solid throughout the oxidation process. Conversely, the oxidized surface of ZS20 without the rare-earth additives comprised a porous ZrO_2 layer up to only 10 micrometers thick covered by amorphous silica, which would have been liquid at 1600°C . The low oxygen permeability of liquid silica suppresses excessive oxidation of ZS20 in static air at 1600°C . However, in a hypersonic air stream this protective advantage would be lost quickly because of liquid silica removal by viscous flow. The oxygen permeabilities of

RE zirconates, although not as low as liquid silica, are still substantially lower than ZrO_2 . This, combined with the high melting point of RE zirconates, suggests that RE additions may be a useful approach to improving the oxidation resistance of UHTCs at intermediate temperatures in hypersonic air flows.

Testing methods and challenges

A large number of testing techniques are available for evaluating the high-temperature performance of UHTC materials. Laser heating/melting has been used extensively to study UHTCs and other ceramics used at extreme temperatures, including refractories and nuclear fuels.¹⁴ Defocused laser heating in air of ZrB_2 - and HfB_2 -based UHTCs was conducted at TWI near Cambridge in the UK using either a Nd:YAG laser, capable of delivering a heat flux of up to approximately 20 megawatts per square meter, or a high-brightness ytterbium fiber laser with a 10-millimeter-diameter collimated beam and able to provide a heat flux up to 44 megawatts per square meter.

Photographs of HfB_2 -based UHTC samples laser tested under various conditions are shown in Figure 6. The top and bottom rows correspond to samples exposed to 8.2 and 15 megawatts per square meter heat flux for 60 seconds, respectively. For the former, the HfB_2 -20-percent-volume-SiC (HS20) sample largely retained its shape and size, but a 100-micrometer-thick white coating developed on the surface that detached from an intermediate oxide layer containing voids or cracks. The HS20-weight-percent- La_2O_3 and HfB_2 samples retained their original shape and size, with the former developing a thin oxide coating and the latter a thicker coating on exposed surfaces. For the 15.2 megawatt per square meter-tested samples, the HfB_2 and HS20-2-weight-percent- La_2O_3 largely retained their integrity, especially when compared with the significant bubbles and craters observed on the HS20.

Typical surface microstructures of HS20- LaB_6 laser-heated for 60 seconds at 15.2 megawatt per square

Figure 7 Surface morphology of HS20-5-weight-percent- LaB_6 sample laser tested for 60 seconds at 15.2 megawatts per square meter, showing (a) dense surface, (b) eutectic microstructure, (c) dendritic structure, (d) submicrometer-sized and nanometer-sized particles, (e) nanoparticles and (f) nanofibers.

meter are shown in Figure 7. Figure 7(a) reveals a dense microstructure—the very high heat flux has modified the structure and morphology of the surface significantly. Figure 7(b) shows a region of the oxidized surface with a eutectic structure that is believed to have been composed of HfB_2 and HfO_2 . EDS analysis confirmed the presence of hafnium, boron and oxygen. Because there is no phase diagram available for this system, the temperature at which this eutectic forms is unknown. Figure 7(c) shows a completely dendritic microstructure, which itself confirms that a large volume of melt was present on the surface. Presumably, because of the subsequent rapid solidification and influence of vapor phases, nanoparticles (Figures 7(d) and (e)) and nanofibers (Figure 7(f)) formed on the surface.

To evaluate the performance of UHTC samples at even higher temperatures, laser testing was performed using an extremely high heat flux of 44 megawatts per square meter, for 1 to 5 seconds, again in air. Figure 8 shows photographs after testing for 1 second. Except for the HfB_2 -2-weight-percent- La_2O_3 sample, all others were severely damaged, losing their shape and uniformity. The surfaces of all samples were black or dark grey in color. This might be attributed either to the solidification of HfB_2 on the top surface (although why it should have survived being oxidized is unknown) or to the formation of a black oxide. The black layer can form as result of the formation of a nonstoichiometric oxide, particularly in the zirconium and hafnium oxide systems. The advantage of adding TaSi_2 to UHTCs to

Figure 8 Photographs of UHTCs tested at 44 megawatts per square meter heat flux for 1 second using a defocused ytterbium laser.

form a black oxide to increase the emissivity is well-known.

Figure 9 shows SEM cross sections of samples laser tested at 44 megawatts per square meter for 1 second. These show that the HfB_2 -2-weight-percent- La_2O_3 sample appeared to perform better than the others, with a thin (approximately 100 micrometers) oxide coating forming and an absence of other defects, such as pores and cracks.

At heat fluxes up to 15.2 megawatts per square meter, HfB_2 -based ceramics perform better in terms of retaining structural integrity compared with ZrB_2 -based ceramics. In addition, SiC reinforcement and lanthanum-based additives

CERAMITEC 2012
Technologies | Innovations | Materials

22 – 25 May 2012
Munich, Germany

Contact: U.S. Office CERAMITEC 2012, Ms. Anika Niebuhr
Tel. 646-437-1014, anieberh@munich-trade-fairs.com

See us at ICACC'12 Expo Booth 402

UHTC composites for hypersonic applications

Figure 9 Comparison of cross-section microstructures of four samples laser tested at 44 megawatts per square meter for 1 second using a defocused ytterbium laser.

Figure 10 Powder distribution across the cross section of a vacuum-impregnated carbon-fiber-HfB₂ composite.

Figure 11 3D micro-CT cross section of a UHTC composite prepared by squeeze impregnation showing powder penetration. The dimensions of the composite were 30-millimeter-diameter 3 18-millimeter-thick. The dark area at the bottom is a hole drilled into the impregnated preform to allow a subsequent CVI stage to deposit carbon.

help to form intermediate layers with low oxygen permeability that appear to slow down the oxidation process. However, at very high heat fluxes, such as 44 megawatts per square meter, microstructural observation indicates that the SiC reinforcement and La₂O₃ additive do not help because they yield gases that further deteriorate the performance of the sample.

Figure 12 EDS mapping of carbon (red), silicon (green) and zirconium (blue) showing the distribution of UHTC powder within a carbon-fiber-ZrB₂-20-volume-percent SiC composite.

UHTC-carbon-fiber composites and hybrid composites

Work at Loughborough is focused on impregnating carbon-fiber-based systems with UHTC powders. Carbon fibers are attractive because they can be formed readily into a preform of almost any configuration by winding, weaving, knitting, braiding or wrapping over a suitably formed mandrel.¹⁵ There have been a number of attempts by researchers to prepare carbon-fiber-based composites for ultra-high-temperature applications. For example, Levine et al.¹⁶ examined composites containing

HfB₂ and SiC powders in a study that also investigated the high-temperature performance of SiC-fiber-reinforced ZrB₂-20-volume-percent-SiC composites (ZSS) at temperatures up to 1927°C for up to 100 minutes.¹⁷ The composites were prepared by a filament winding and slurry impregnation technique followed by hot pressing, and results were compared with ZrB₂-20-volume-percent-SiC and ZrB₂-14-volume-percent-SiC-30-volume-percent-carbon compositions containing no fiber reinforcement. Tang et al.¹⁸ prepared various carbon-fiber UHTC powder composites using 2D carbon-fiber preforms and aqueous UHTC powder slurries based on ZrB₂, SiC, HfC and TaC, which were infiltrated into the preforms using a pressure-assisted technique. The impregnated composites were further densified by pyrocarbon deposition at 1000°C to 1100°C using a chemical vapor infiltration process. The UHTC powders concentrated in a 2-millimeter-deep layer at the surface. High-temperature oxidation performance of the composites was measured using an oxyacetylene flame, and the ZrB₂-based system displayed the best resistance after 30 seconds at 3920 kilowatts per square meter and 2700°C. Addition of SiC was found to improve the oxidation resistance only under the less demanding conditions of 2380 kilowatts per square meter and 1800°C, albeit they were able to survive for 300 seconds.

Hybrid UHTC composites were fabricated at Loughborough using 30-millimeter-diameter 3 20-millimeter-thick 2.5 D carbon-fiber preforms that contained 23-volume-percent fibers provided by Surface Transforms Ltd. in the UK. UHTC powder/phenolic resin/acetone slurries were prepared by ball milling using alumina milling media for 48 hours. The UHTC compositions included ZrB₂, ZrB₂-20-volume-percent-SiC, ZrB₂-20-volume-percent-SiC-10-volume-percent-LaB₆, HfB₂ and HfC while the phenolic resin had a carbon content of 45.5 percent. The carbon-fiber preforms were separately impregnated with the slurries using either a squeeze or vacuum impregnation technique and then dried in an

Figure 13 Comparison of carbon-carbon (CC) and carbon-fiber (Cf-) UHTC composites after 60 seconds oxyacetylene testing. Diameter of the composites was 30 millimeters.

Figure 14 TEM images of (a) HfC particles and (b) HfB₂ particles synthesized using a sol-gel approach.

oven at 75°C for 4 hours followed by curing at 125°C to 150°C for 2 hours. This cycle was repeated three times to maximize the amount of UHTC powder within each composite. After the third impregnation and curing, the samples were pyrolyzed at 900°C under flowing argon (99.998 percent pure) and further densified using chemical vapor infiltration of carbon. Benchmark carbon/carbon composites also were prepared using chemical vapor infiltration of the preforms without UHTC powder

of techniques, including SEM, EDX and micro-CT to determine the depth of impregnation, powder distribution and the efficiency of powder mixing. The bulk density of the composites was measured using geometrical methods. The powder distribution across the cross section of a carbon-fiber-HfB₂ UHTC composite (Figure 10) reveals that the preforms were fully impregnated from top to bottom, although the composites were found to be slightly denser near the circumference because of the UHTC powder slurry impregnation from the sides of the preform. Micro-CT analysis was performed on the impregnated preforms to determine the depth of penetration. A representative 3D cross-sectional image is given in Figure 11 of one of the carbon-fiber-ZrB₂ composites. The depth of impregnation was found to be approximately 7 millimeters from the top surface, which is greater than the 2–3 millimeter penetration achieved by Tang et al.¹⁸ Powder distribution results obtained using EDS analysis on the cross section of carbon-fiber-ZrB₂-2SiC composites revealed uniform mixing and distribution of the powder within the composite (Figure 12). In general, it was found that the vacuum impregnation technique yielded superior results to the squeeze impregnation route.

High-temperature performance of the composites was determined using an oxyacetylene torch test facility constructed at Loughborough University (see sidebar). Initially, the aim was

Figure 15 Carbon-fiber-HfB₂ composites after oxyacetylene torch testing after (a) 60 seconds showing negligible erosion and (b) 140 seconds showing less than 2-millimeter erosion.

impregnation. The resulting composites were examined using a range

simply to rank the UHTC composites according to their oxidation performance. However, subsequently the test was used to aid the development of superior composites.

The images of the preliminary composites after 60 seconds oxyacetylene torch testing are compared in Figure 13. As expected, the carbon-carbon composite was damaged over a wide area, approximately 20-millimeter-diameter damage zone, while the performances of the carbon-fiber-ZrB₂ and carbon-fiber-ZrB₂-20-volume-percent-SiC composites were similar to each other, with the damage being mainly focused over an approximately 5-millimeter-diameter area. There was more erosion damage for the LaB₆ composite compared with the other ZrB₂-containing composites. The high-temperature flame penetrated the impregnated layer and attacked the carbon-carbon layer below. The addition of LaB₆ was intended to improve the oxidation resistance through the formation of La₂Zr₂O₇, pyrochlore structures at higher temperatures.¹⁰

Carbon-fiber-HfB₂ and carbon-fiber-HfC composites offered the best erosion protection, even though the UHTC powders were oxidized to HfO₂ as expected. The presence of molten phases can be seen on all of the impregnated composites, independently confirming the temperature of the flame. The amount of melting was much lower in the HfB₂-based composites than in those based on ZrB₂ because of the higher melting temperature of HfO₂ (approximately 2800°C).¹¹ The oxide layer formed on the carbon-fiber-HfC composite was less adherent than those on the other composites and fell off after the test, possibly because of the

UHTC composites for hypersonic applications

absence of any glassy phases during the test and the build up of CO/CO₂ gas below the oxide layer.

Based on the initial tests, further research was focused on the two hafnium-based compositions because they showed the best high-temperature performance. Attempts were made to improve the UHTC slurry impregnation, and the lack of availability of HfC and HfB₂ powders with submicrometer particle size was an issue. The average particle sizes of HfC and HfB₂ from the two major European suppliers were more than 1 micrometer. Hence, research was initiated at Loughborough University to synthesize nanometer-sized HfC and HfB₂ particles using sol-gel routes, which has now been achieved (Figure 14).¹⁹

Composites also were prepared by mixing powders of various particle sizes. The average bulk densities of the composites were 2.4 and 2.2 grams per cubic centimeter for HfB₂- and HfC-based composites, respectively, which is higher than the densities achieved with commercial powder alone. With the powder mixture and using vacuum impregnation, it is now possible to prepare carbon-fiber-HfB₂ composites that show no erosion after 60 seconds at approximately 2700°C and minimum erosion after 140 seconds at the same temperature (Figure 15).²⁰

Thus, the UHTC powder-impregnated carbon-fiber composites offer excellent high-temperature oxidation protection when tested using an oxyacetylene torch. Current efforts focus on determining the mechanical properties of UHTC composites at room and elevated temperatures and on the preparation of sharp leading-edge-shaped composites for performance testing. Trials also are in progress to sinter the impregnated composites using the SPS technique. Another novel approach being evaluated is the preparation of hybrid UHTC composites incorporating a UHTC monolithic layer to further improve the high-temperature oxidation resistance.

Summary and future work

Real progress has been made in the quest to develop materials capable

of withstanding the difficult conditions for hypersonic space travel. UHTC research at Imperial College and Loughborough University has demonstrated the preparation of fully dense UHTC monoliths for a range of various compositions and of carbon-fiber-UHTC composites with significant powder impregnation. Key aspects include the following.

- The microstructures formed at UHTs are complex and heterogeneous.
- Thermal diffusivities in composite systems tend to merge to similar values at UHTs, whereas CTEs remain comparatively large.
- At high heat fluxes (approximately 44 megawatts per square meter) SiC and lanthanum-based additives lead to gas evolution and deterioration in laser test performance.
- The oxyacetylene torch test is useful for rapid screening of UHTC composites based on UHT oxidation performance.
- Carbon-fiber-HfB₂ composites showed the best oxidation resistance above 2500°C.
- Nanocrystalline HfB₂ and HfC powders have been synthesised using sol-gel routes and will be impregnated into carbon-fiber preforms.

Future work will be focused primarily on joining UHTC monoliths with the UHTC composites to take maximum advantage of the two approaches. The goal is to prepare prototype leading edge components and plates for subsequent in-flight testing. ■

Acknowledgements

The authors thank the UK's Defence Science and Technology Laboratory (DSTL) for providing the financial support for this work under contract numbers DSTLX-1000015267 and DSTLX-1000015413 as well as the US Air Force Research Laboratory's Materials and Manufacturing Directorate for ongoing collaborations.

About the authors

A. Paul, S. Venugopal, J. Binner and B. Vaidhyanathan are affiliated with the Department of Materials, Loughborough University, Loughborough, UK. D.D. Jayaseelan,

E. Zapata-Solvas and W.E. Lee are affiliated with the Centre for Advanced Structural Ceramics, Department of Materials, Imperial College London, S Kensington Campus, London, UK. A. Heaton and P. Brown are affiliated with DSTL, Porton Down, Wiltshire, UK. Corresponding authors: W.E. Lee, w.e.lee@imperial.ac.uk; J. Binner, j.binner@boror.ac.uk

References

- ¹C. Tallon, S. Slater, A. Gillen, C. Wood and J. Turner, "Ceramic Materials for Hypersonic Applications," *Materials Australia*, [July] 28–32 (2011).
- ²K. Forsthoefel and L.G. Sneddon, "Precursor Routes to Group 4 Metal Borides, and Metal Boride/Carbide and Metal Boride/Nitride Composites," *J. Mater. Sci.*, 39 [19] 6043–49 (2004).
- ³E. Wuchina, M. Opeka, S. Causey, K. Buesking, J. Spain, A. Cull, J. Routbort and E. Gutierrez-Mora, "Designing for Ultrahigh-Temperature Applications: The Mechanical and Thermal Properties of HfB₂, HfC, HfN_x and alpha-Hf(N)," *J. Mater. Sci.*, 39 [19] 5939–49 (2004).
- ⁴F. Monteverde and A. Bellosi, "Oxidation of ZrB₂-Based Ceramics in Dry Air," *J. Electrochem. Soc.*, 150 [11] B552–B559 (2003).
- ⁵W.G. Fahrenholtz, G.E. Hilmas, A.L. Chamberlain and J.W. Zimmermann, "Processing and Characterization of ZrB₂-Based Ultra-High-Temperature Monolithic and Fibrous Monolithic Ceramics," *J. Mater. Sci.*, 39 [19] 5951–57 (2004).
- ⁶E.J. Wuchina and M.M. Opeka, "Oxidation of Hf-Based Ceramics," *High-Temperature Corrosion and Materials Chemistry*, 99 [38] 477–88 (2000).
- ⁷A.G. Metcalfe, N.B. Elsner, D.T. Allen, E. Wuchina, M. Opeka and E. Opila, "Oxidation of Hafnium Diboride," *High Temperature Corrosion and Materials Chemistry*, 99 [38] 489–501 (2000).
- ⁸E. Eakins, D.D. Jayaseelan and W.E. Lee, "Toward Oxidation-Resistant ZrB₂-SiC Ultra-High-Temperature Ceramics," *Metall. Mater. Trans. A-Phys. Metall. Mater. Sci.*, 42A, 878–87 (2011).
- ⁹E.J. Opila and M.C. Halbig, "Oxidation of ZrB₂-SiC," pp. 221–28 in 25th Annual Conference on Composites, Advanced Ceramics, Materials, and Structures: A: Ceramic Engineering and Science Proceedings, Vol. 22, Issue 3. Edited by M. Singh and T. Jessen. Wiley, New York, 2001. (Published online March 28, 2008.)
- ¹⁰D.D. Jayaseelan, E. Zapata-Solvas, P. Brown and W.E. Lee, "In-Situ Formation of Oxidation-Resistant Refractory Coatings on SiC-Reinforced ZrB₂ Ultra-High-Temperature Ceramics (UHTCs)," *J. Am. Ceram. Soc.* (to be published 2012).
- ¹¹T.A. Parthasarathy, R.A. Rapp, M. Opeka and R.J. Kerans, "A Model for the Oxidation of ZrB₂, HfB₂ and TiB₂," *Acta Mater.*, 55, 5999–6010 (2007).
- ¹²F. Monteverde, "Progress in the Fabrication of Ultra-High-Temperature Ceramics: In-Situ Synthesis, Microstructure and Properties of a Reactive Hot-Pressed HfB₂-SiC Composite," *Compos. Sci. Technol.*, 65 [11–12] 1869–79 (2005).
- ¹³E. Zapata-Solvas, D.D. Jayaseelan, P. Brown and W.E. Lee, unpublished work.
- ¹⁴H.F. Jackson, D.D. Jayaseelan, D. Manara, C.P. Casoni and W.E. Lee, "Laser Melting of Zirconium Carbide: Determination of Phase Transitions in Refractory Ceramic Systems," *J. Am. Ceram. Soc.*, 94 [10] 3561–69 (2011).
- ¹⁵A. Sayir, "Carbon-Fiber-Reinforced Hafnium Carbide Composite," *J. Mater. Sci.*, 39, 5995–6003 (2004).
- ¹⁶S.R. Levine, E.J. Opila, R.C. Robinson and J.A. Lorincz, "Characterization of an Ultra-High-Temperature Ceramic Composite," NASA Report No. TM 2004-213085, 2004.
- ¹⁷S.R. Levine, E.J. Opila, M.C. Halbig, J.D. Kiser, M. Singh and J.A. Salem, "Evaluation of Ultra-High-Temperature Ceramics for Aeropropulsion Use," *J. Eur. Ceram. Soc.*, 22 [14–15] 2757–67 (2002).
- ¹⁸S.F. Tang, J.Y. Deng, S. Wang, W.C. Liu, and K. Yang, "Ablation Behaviors of Ultra-High-Temperature Ceramic Composites," *Mater. Sci. Eng. A*, 465, 1–7 (2007).
- ¹⁹S. Venugopal, A. Paul, B. Vaidhyanathan, J. Binner, A. Heaton and P. Brown, "Nano-Crystalline Ultra-High-Temperature HfB₂ and HfC Powders and Coatings Using a Sol-Gel Approach," *Advanced Ceramic Coatings and Materials for Extreme Environments: Ceram. Eng. Sci. Proc.*, Volume 32, Edited By D. Zhu, H-T. Lin, Y. Zhou, S. Widjaja and D. Singh, Ed.
- ²⁰A. Paul, S. Venugopal, J. Binner, B. Vaidhyanathan, A. Heaton and P. Brown, "Effect of UHTC Powder Particle Size and Preform Fibre Orientation on the High-Temperature Performance of UHTC Composites," (submitted *J. Eur. Ceram. Soc.* 2011).

Oxyacetylene torch testing of materials

Many testing techniques are available for evaluating high-temperature performance of UHTC materials, including static furnace oxidation testing, laser ablation testing, oxyacetylene torch testing, plasma wind tunnel testing, strip heater testing, arc jet testing and scramjet testing.* None of these test methods alone can reproduce all the conditions experienced during hypersonic flight. Oxyacetylene torch testing, however, is a quick and inexpensive technique to evaluate the high-temperature performance of materials.

At Loughborough University in the UK, an oxyacetylene-torch-testing facility has been built that is equipped to perform high-temperature oxidation testing of UHTC materials at temperatures up to about 2800°C, while recording the temperature and temperature distribution during testing (Figure 1). Heating rates of up to approximately 500°C per second can be achieved.

An oxygen-rich flame was chosen for testing the composites, and this was achieved by supplying stoichiometrically excess oxygen: acetylene to oxygen ratio is 1:1.35. The UHTC samples are fixed in a water-cooled graphite holder with three graphite bolts. To date, tests have been conducted for 30 seconds up to 360 seconds, although tests of shorter or longer duration are possible. During the test, the temperature is measured using a two-color pyrometer (Marathon MR1SCSF, Raytek GmbH, Berlin, Germany), and the temperature distribution is measured using an infrared thermal-imaging camera (Thermovision A40 FLIR Systems AB, Danderyd, Sweden). The two-color pyrometer is capable of recording temperatures up to 3000°C, and the thermal imaging camera can record temperatures up to 1500°C. By adding an IR neutral density filter, the camera can record temperatures up to 2800°C. The back surface temperature of the samples is recorded using a K-type thermocouple connected to a data logger.

Figure 2 shows an image taken during the oxyacetylene torch testing of one of the UHTC composites along with another image taken immediately after extinguishing the flame. It is a very aggressive test because it involves high temperature, high-velocity gas flow and oxidizing gases.

The temperature distribution recorded

Figure 1 Oxyacetylene test set up at Loughborough University: (1) back face thermocouple, (2) water cooling system, (3) sample holder, (4) sample, (5) sample guide, (6) protective insulation, (7) oxyacetylene torch, (8) neutral density filter, (9) thermal imaging camera and (10) two-color pyrometer.

during a 6-minute testing of a UHTC composite is shown in Figure 3. The figure shows a very high temperature gradient, and the composite samples survived without much damage.

Planned improvements include increasing the temperature capability and uniformity of the torch by using a multiflame nozzle, adding a computer controller to automate the whole testing process, including sample movement, and the ability to provide rapid cooling via applying a jet of cold nitrogen gas.

Figure 2 Image showing (a) sample being tested using an oxyacetylene flame and (b) immediately after the test.

Figure 3 Temperature distribution during oxyacetylene torch testing: (a) beginning of the test, (b) at 3 minutes, (c) at 6 minutes and (d) immediately after extinguishing the flame.

*References covering each of these techniques are available in the electronic edition of the *Bulletin*, which can be viewed at www.ceramics.org>The Bulletin.

References

- ¹I.G. Talmy, J.A. Zaykoski and C.A. Martin, "Flexural creep deformation of ZrB₂/SiC Ceramics in Oxidizing Atmosphere," *J. Am. Ceram. Soc.*, 91, 1441-7 (2008).
- ²I.G. Talmy, J.A. Zaykoski and M.M. Opeka, "High-Temperature Chemistry and Oxidation of ZrB₂ Ceramics Containing SiC, Si₃N₄, Ta₃Si₃, and TaSi₂," *J. Am. Ceram. Soc.*, 91, 2250-7 (2008).
- ³D. Sciti, V. Medri and L. Silvestroni, "Oxidation Behaviour of HfB₂-15 vol.% TaSi₂ at Low, Intermediate and High Temperatures," *Scr. Mater.*, 63, 601-4 (2010).
- ⁴C. Carney, "Oxidation Resistance of Hafnium Diboride-Silicon Carbide from 1400 to 2000°C," *J. Mater. Sci.*, 44, 5673-81 (2009).
- ⁵C.M. Carney, P. Mogilvesky and T.A. Parthasarathy, "Oxidation Behavior of Zirconium Diboride Silicon Carbide Produced by the Spark Plasma Sintering Method," *J. Am. Ceram. Soc.*, 92, 2046-52 (2009).
- ⁶C.M. Carney, T.A. Parthasarathy and M.K. Cinibulk, "Oxidation Resistance of Hafnium Diboride Ceramics with Additions of Silicon Carbide and Tungsten Boride or Tungsten Carbide," *J. Am. Ceram. Soc.*, 94, 2600-7 (2011).
- ⁷W. Han, P. Hu, X. Zhang, J. Han and S. Meng, "High-Temperature Oxidation at 1900°C of ZrB₂-xSiC Ultrahigh-Temperature Ceramic Composites," *J. Am. Ceram. Soc.*, 91, 3328-34 (2008).
- ⁸P. Hu, X. Zhang, J. Han, X. Luo and S. Du, "Effect of Various Additives on the Oxidation Behavior of ZrB₂-Based Ultra-High-Temperature Ceramics at 1800°C," *J. Am. Ceram. Soc.*, 93, 345-9 (2010).
- ⁹P. Lespade, N. Richet and P. Goursat, "Oxidation Resistance of HfB₂-SiC Composites for Protection of Carbon-Based Materials," *Acta Astronaut.*, 60, 858-64 (2007).
- ¹⁰R. Licheri, R. Oru, C. Musa, A. Locci and G. Cao, "Spark Plasma Sintering of ZrB₂- and HfB₂-Based Ultra High Temperature Ceramics Prepared by SHS," *International Journal of Self-Propagating High-Temperature Synthesis*, 18, 15-24 (2009).
- ¹¹M. Mallik, K.K. Ray and R. Mitra, "Oxidation Behavior of Hot Pressed ZrB₂-SiC and HfB₂-SiC Composites," *J. Eur. Ceram. Soc.*, 31, 199-215 (2011).
- ¹²F. Monteverde and A. Bellosi, "The Resistance to Oxidation of an HfB₂-SiC Composite," *J. Eur. Ceram. Soc.*, 25, 1025-31 (2005).
- ¹³D. Ni, G. Zhang, F. Xu and W. Guo, "Initial Stage of Oxidation Process and Microstructure Analysis of HfB₂-20 vol.% SiC Composite at 1500°C," *Scr. Mater.*, 64, 617-20 (2011).
- ¹⁴H. Petla, E.P. Renova, A. Bronson, J.F. Chessa and N. Maheswarajah, "A Computational Analysis of a ZrO₂-SiO₂ Scale for a ZrB₂-ZrC-Zr Ultrahigh Temperature Ceramic Composite System," *J. Eur. Ceram. Soc.*, 30, 2407-18 (2010).
- ¹⁵A. Rezaie, W.G. Fahrenholtz and G.E. Hilmas, "Oxidation of Zirconium Diboride-Silicon Carbide at 1500°C at a Low Partial Pressure of Oxygen," *J. Am. Ceram. Soc.*, 89, 3240-5 (2006).
- ¹⁶C. Tian, D. Gao, Y. Zhang, C. Xu, Y. Song and X. Shi, "Oxidation Behaviour of Zirconium Diboride-Silicon Carbide Ceramic Composites under Low Oxygen Partial Pressure," *Corros. Sci.*, In Press, Corrected Proof.
- ¹⁷M. Wang, C. Wang, L. Yu, Y. Huang and X. Zhang, "Oxidation Behavior of SiC Platelet-Reinforced ZrB₂ Ceramic Matrix Composites," *Int. J. Appl. Ceram. Techn.*, DOI:10.1111/j.1744-7402.2011.02647.x, (2011).
- ¹⁸X. Zhang, L. Xu, S. Du, W. Han and J. Han, "Preoxidation and Crack-Healing Behavior of ZrB₂-SiC Ceramic Composite," *J. Am. Ceram. Soc.*, 91, 4068-73 (2008).
- ¹⁹H.F. Jackson, D.D. Jayaseelan, W.E. Lee, et al., "Laser Melting of Spark Plasma-Sintered Zirconium Carbide: Thermophysical Properties of a Generation IV Very High-Temperature Reactor Material," *Int. J. Appl. Ceram. Techn.*, 7, 316-26 (2010).
- ²⁰H.F. Jackson, D.D. Jayaseelan, D. Manara, C.P. Casoni and W.E. Lee, "Laser Melting of Zirconium Carbide: Determination of Phase Transitions in Refractory Ceramic Systems," *J. Am. Ceram. Soc.*, 94, 3561-69 (2011).
- ²¹Z. Chen, D. Fang, Y. Miao and B. Yan, "Comparison of Morphology and Microstructure of Ablation Centre of C/SiC Composites by Oxy-Acetylene Torch at 2900 and 3550°C," *Corros. Sci.*, 50, 3378-81 (2008).
- ²²Z. Chen and B. Yan, "Morphology and Microstructure of Three-Dimensional Orthogonal C/SiC Composites Ablated by an Oxyacetylene Flame at 2900°C," *Int. J. Appl. Ceram. Techn.*, 6, 164-70 (2009).
- ²³S.R. Levine, E.J. Opila, R.C. Robinson and J.A. Lorincz, "Characterization of an Ultra-High Temperature Ceramic Composite," *NASA TM-2004-213085*, 1-26 (2004).
- ²⁴J.C. Han, X.D. He and S.Y. Du, "Oxidation and Ablation of 3D Carbon-Carbon Composite at up to 3000°C," *Carbon*, 33, 473-8 (1995).
- ²⁵J. Han, P. Hu, X. Zhang, S. Meng and W. Han, "Oxidation-Resistant ZrB₂-SiC Composites at 2200°C," *Composites Sci. Technol.*, 68, 799-806 (2008).
- ²⁶X. Li, J. Shi, H. Zhang, G. Zhang, Q. Guo and L. Liu, "Ablation Resistance and Mechanical/Conductive Properties of ZrB₂ Reinforced Carbon Based Composites," *Journal of Composite Materials*, 41, 353-66 (2007).
- ²⁷P. Mark, "Oxidation Resistant HfC-TaC Rocket Thruster for High Performance Propellants," *NASA report NAS3-27272*, 1-24 (1999).
- ²⁸G.M. Song, Y.J. Wang and Y. Zhou, "Elevated Temperature Ablation Resistance and Thermophysical Properties of Tungsten Matrix Composites Reinforced with ZrC particles," *J. Mater. Sci.*, 36, 4625-31 (2001).
- ²⁹G. Song, Y. Zhou and Y. Wang, "Effect of Carbide Particles on the Ablation Properties of Tungsten Composites," *Mater. Charact.*, 50, 293-303 (2003).
- ³⁰S. Tang, J. Deng, S. Wang, W. Liu and K. Yang, "Ablation Behaviors of Ultra-High Temperature Ceramic Composites," *Materials Science and Engineering: A*, 465, 1-7 (2007).
- ³¹F. Monteverde and R. Savino, "Stability of Ultra-High-Temperature ZrB₂-SiC Ceramics Under Simulated Atmospheric Re-Entry Conditions," *J. Eur. Ceram. Soc.*, 27, 4797-805 (2007).
- ³²F. Monteverde, R. Savino, M.D.S. Fumo and A. Di Maso, "Plasma Wind Tunnel Testing of Ultra-High Temperature ZrB₂-SiC Composites Under Hypersonic Re-Entry Conditions," *J. Eur. Ceram. Soc.*, 30, 2313-21 (2010).
- ³³R. Savino, M. De Stefano Fumo, D. Paterna, A. Di Maso and F. Monteverde, "Arc-Jet Testing of Ultra-High-Temperature-Ceramics," *Aerospace Science and Technology*, 14, 178-87 (2010).
- ³⁴S.N. Karlsdottir, J.W. Halloran, F. Monteverde and A. Bellosi, "Oxidation

of $\text{ZrB}_2\text{-SiC}$: Comparison of Furnace Heated Coupons and Self-Heated Ribbon Specimens," pp. 327-36 in *Mechanical Properties and Performance of Engineering Ceramics and Composites III*. John Wiley & Sons, Inc., 2007; 2009.

³⁵S.N. Karlsdottir and J.W. Halloran, "Rapid Oxidation Characterization of Ultra-High Temperature Ceramics," *J Am Ceram Soc.*, 90, 3233-8 (2007).

³⁶S. Gangireddy, S.N. Karlsdottir, S.J. Norton, J.C. Tucker and J.W. Halloran, "In Situ Microscopy Observation of Liquid Flow, Zirconia Growth, and CO Bubble Formation during High Temperature Oxidation of Zirconium Diboride-Silicon Carbide," *J. Eur. Ceram. Soc.*, 30, 2365-74 (2010).

³⁷M. Gasch, D. Ellerby, E. Irby, S. Beckman, M. Gusman and S. Johnson, "Processing, Properties and Arc Jet Oxidation of Hafnium Diboride/Silicon Carbide Ultra High Temperature Ceramics," *J. Mater. Sci.*, 39, 5925-37 (2004).

³⁸E. Opila, S. Levine and J. Lorincz, "Oxidation of ZrB_2 - and HfB_2 -Based Ultra-High Temperature Ceramics: Effect of Ta Additions," *J. Mater. Sci.*, 39, 5969-77 (2004).

³⁹X. Zhang, P. Hu, J. Han and S. Meng, "Ablation Behavior of $\text{ZrB}_2\text{-SiC}$ Ultra High Temperature Ceramics under Simulated Atmospheric Re-Entry Conditions," *Composites Sci. Technol.*, 68, 1718-26 (2008).

⁴⁰T.H. Squire and J. Marschall, "Material Property Requirements for Analysis and Design of UHTC Components in Hypersonic Applications," *J. Eur. Ceram. Soc.*, 30, 2239-51 (2010).

⁴¹T.A. Parthasarathy, M.D. Petry, G. Jefferson, M.K. Cinibulk, T. Mathur and M.R. Gruber, "Development of a Test to Evaluate Aerothermal Response of Materials to Hypersonic flow Using a Scramjet Wind Tunnel," *Int. J. Appl. Ceram. Techn.*, 8, 832-47 (2011).